

TECHNICAL DATA SHEET

TECHNYL C 246SIL1 GN 6080
(Previously DOMAMID 6IK4UV1 GN66080)

Polyamide 6, UV-stabilized, low temperature impact modified, for injection moulding

General

Feature	Low temperature impact modified	UV-stabilized
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Colors available	Black	Grey
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-I
ISO 16396 designation	PA6-I,M1L1,S14-020

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.06
Molding shrinkage, parallel		ISO 294-4, 2577	%	1.55 - 1.7
Molding shrinkage, normal		ISO 294-4, 2577	%	2.1 - 2.3

TECHNICAL DATA SHEET

TECHNYL C 246SIL1 GN 6080

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	1850 / -
Stress at break		ISO 527-1/-2	MPa	35 / -
Strain at break		ISO 527-1/-2	%	20 / -
Yield stress		ISO 527-1/-2	MPa	45 / -
Yield strain		ISO 527-1/-2	%	4 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	1600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	60 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU		NB / NB
Charpy impact strength, -30°C	-30°C	ISO 179/1eU		NB / NB
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	70 / -
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m²	25 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m²	NB / -
Izod impact strength, -30°C	NB	ISO 180/1U	kJ/m²	-1 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	65 / -
Izod notched impact strength, -30°C	-30°C	ISO 180/1A	kJ/m²	20 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	170
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	55
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	155

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+013

Burning behaviour

Flammability, 0.75 mm	0.75 mm	UL 94		HB
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		<100

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	240 - 260 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For unfilled polyamides, Domo recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.