

TECHNICAL DATA SHEET

TECHNYL D 218 V30 BK
(Previously TECHNYL EXTEN D 218 V30 BLACK)



TECHNYL D 218 V30 BK is a polyamide 6.10, reinforced with 30% of glass fibre, heat stabilized, for injection moulding. This grade offers excellent chemical resistance, low water absorption, very good mechanical properties and moldability. It is a partially bio-sourced material.

General

Feature	Heat-aging stabilized Contains renewable content	Chemical resistant Low moisture absorption
Polymer type	PA610 (Polyamide 610)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Applications	Connectors PC / laptop / tablet	home & office furniture
Colors available	Black	Natural
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA610-GF30
-----------------------	------------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.3
Water absorption	24 hr, 23°C	ISO 62	%	0.38
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.3
Molding shrinkage, normal		ISO 294-4, 2577	%	0.8

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	8900 / 5500
Stress at break		ISO 527-1/-2	MPa	150 / 80
Strain at break		ISO 527-1/-2	%	4.1 / 8
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	90 / 85
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	85 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	13 / -

TECHNICAL DATA SHEET

TECHNYL D 218 V30 BK

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	215
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	216
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	198

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	240 - 250 °C
Middle temperature	245 - 255 °C
Front temperature	250 - 260 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.