

TECHNICAL DATA SHEET

TECHNYL PROTECT C 60 S30 GY R7001
(Previously DOMAMID FR 6B30V0E 124)

Polyamide 6, 30% glass beads, halogen and red phosphorus free flame retardant, heat-aging stabilized, for injection moulding

General

Feature	UL V0 Heat-aging stabilized	Halogen and red phosphorus free flame retardant
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	

Product identification

ISO 1043 abbreviation	PA6-GB30 FR(40)
ISO 16396 designation	PA6,GB30FR(40),M1H,S14-050

	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm³	1.41
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.8 - 1
Molding shrinkage, normal		ISO 294-4, 2577	%	0.9 - 1.1
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm³/10 min	100
Viscosity number	96% H2SO4	ISO 307	cm³/g	130

Physical properties

Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	5200 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	50 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	2 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	5000 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	90 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	15 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	3 / -
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m²	15 / -
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	3 / -

TECHNICAL DATA SHEETTECHNYL PROTECT C 60 S30 GY R7001

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	175
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	75
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	200

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+016
Surface resistivity		IEC 62631-3-1	ohm	1E+014
Comparative tracking index	Solution A	IEC 60112	V	600
CTI performance level category		Sol A		PLC 0

Burning behaviour

Flammability, 1.5 mm	1.5 mm	UL 94		V0
Glow-wire flammability index, GWFI	1-3 mm	IEC 60695-2-12	°C	960
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	230 - 260 °C
Recommended mould temperature	80 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.