

TECHNICAL DATA SHEET

TECHNYL PURE A 216E1 V25 BK

(Previously TECHNYL A 216E1 V25 BLACK)

TECHNYL PURE A 216E1 V25 BK is a polyamide 66, reinforced with 25% of glass fiber, for injection moulding. This grade offers a formula clean from additive that contains halogen and other substances (ex: phosphorous) that can migrate and generate corrosion issues. Electrofriendly grade. Suitable for laser printing. < 50ppm halogen content guaranteed, based on internal elution analysis.

General

Feature	Lasermarkable		Electro-friendly
Polymer type	PA66 (Polyamide 66)		
Processing technology	Injection molding		
Certification	RoHS		EC 1907/2006 (REACH)
Applications	Automotive Applications Electrical/Electronic Applications fuel cell / H2 system		Connectors Overmolding
Colors available	Black		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA66-GF25
-----------------------	-----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.32
Water absorption	24 hr, 23°C	ISO 62	%	0.9

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	8400 / 6300
Stress at break		ISO 527-1/-2	MPa	165 / 120
Strain at break		ISO 527-1/-2	%	3 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	7300 / 5000
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	57 / 87
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	10 / 13
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	8.5 / 15

TECHNICAL DATA SHEET

TECHNYL PURE A 216E1 V25 BK

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	263
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	255

Flammability, 1.5 mm	1.5 mm	UL 94		HB
Flammability, 3.0 mm	3.0 mm	UL 94		HB
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650
Oxygen index			%	23

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.