

TECHNICAL DATA SHEET

TECHNYL SAFE C 216FC V30 NC
(Previously DOMAMID 6G30FC 300 NC)

TECHNYL SAFE C 216FC V30 NC is a polyamide 6, 30% glass fiber reinforced, food contact approved for injection moulding. Designed to be used in moulded parts requiring food contact compliance in industrial, consumer good as well as appliance applications.

General

Feature	Food contact approved	
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS EC 1907/2006 (REACH)	UL-Yellow Card WRAS BS6920-1: 2000 and 2014
Applications	Small appliance Industrial Applications large appliance	Consumer good application building / construction
Colors available	Natural	
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF30
ISO 16396 designation	PA6,GF30,M1,S14-090

	Condition	Standard	Unit	Value
Physical properties				
Density		ISO 1183	g/cm³	1.36
Humidity absorption	T=23°C, 50% RH	ISO 62	%	2.1
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.25 - 0.45
Molding shrinkage, normal		ISO 294-4, 2577	%	0.85 - 1.05
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg	ISO 1133	cm³/10 min	40
Viscosity number	96% H2SO4	ISO 307	cm³/g	145

TECHNICAL DATA SHEET

TECHNYL SAFE C 216FC V30 NC

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9500 / 5300
Stress at break	5 mm/min	ISO 527-1/-2	MPa	170 / 110
Strain at break	5 mm/min	ISO 527-1/-2	%	4 / 9
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	7200 / 4500
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	270 / 150
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	95 / 110
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m²	75 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	14 / 25
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m²	11 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	220
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	205
Vicat softening temperature	50°C/h - 50N	ISO 306	°C	214

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+013
Surface resistivity		IEC 62631-3-1	ohm	1E+014
Comparative tracking index	Solution A	IEC 60112	V	500
CTI performance level category		Sol A		PLC 1

Burning behaviour

UL Yellow Card availability 	Click here to have access to the UL Yellow Card → QMFZ2.E44716			
Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min

Test run at 23°C if not differently specified, DAM state (dry as moulded).
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	250 - 290 °C
Recommended mould temperature	80 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.