

**TECHNICAL DATA SHEET**

**TECHNYL STAR AFX 218 V60 BK 31N**

TECHNYL STAR AFX 218 V60 BK 31N is a high flow polyamide 66 resin, reinforced with 60% of glass fibre, heat stabilized, for injection moulding. Due to its outstanding flow characteristics, this grade shows exceptional processing behaviour and excellent surface aspect of the finished part.

**General**

Feature	Heat-aging stabilized Very high flow High stiffness	High dimensional stability Excellent surface finish
Polymer type	PA66 (Polyamide 66)	
Processing technology	Injection molding	
Certification	RoHS EC 1907/2006 (REACH)	UL-Yellow Card
Applications	Automotive Applications Handles	Consumer good application Industrial Applications
Colors available	Black	Natural
Forms	Pellets	

**Product identification**

ISO 1043 abbreviation	PA66-GF60
-----------------------	-----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

**Physical properties**

Density		ISO 1183	g/cm <sup>3</sup>	1.69
Water absorption	24 hr, 23°C	ISO 62	%	0.6
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.35
Molding shrinkage, normal		ISO 294-4, 2577	%	0.6

TECHNICAL DATA SHEET

TECHNYL STAR AFX 218 V60 BK 31N

	Condition	Standard	Unit	Value dam / cond.*
<b>Mechanical properties</b>				
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	22000 / 16500
Stress at break		ISO 527-1/-2	MPa	270 / 195
Strain at break		ISO 527-1/-2	%	2.1 / 3.1
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	20000 / 15000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	410 / 300
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	95 / 90
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	17 / 18
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m²	94 / 92
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m²	17 / 20

**Thermal properties**

Melting temperature, 10°C/min		ISO 11357-1	°C	262
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	255

**Electrical properties**

Volume resistivity		IEC 62631-3-1	ohm.m	1E+012
Surface resistivity		IEC 62631-3-1	ohm	1E+013
Comparative tracking index	Solution A	IEC 60112	V	550
CTI performance level category		Sol A		PLC 1
Dielectric strength	1 mm	IEC 60243-1	kV/mm	40

**Burning behaviour**

UL Yellow Card availability 	Click here to have access to the UL Yellow Card → <a href="#">QMFZ2.E44716</a>
---	--

\*: conditioned according to ISO 1110

**Processing conditions**

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	265 - 275 °C
Middle temperature	270 - 280 °C
Front temperature	280 - 290 °C
Recommended mould temperature	60 - 90 °C

**TECHNICAL DATA SHEET**

**TECHNYL STAR AFX 218 V60 BK 31N**

**Injection notes**

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

**Injection advice**

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

**Disclaimer**

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.