

TECHNICAL DATA SHEET

TECHNYL STAR S 216 V35 NC

TECHNYL STAR S 216 V35 NC is based on a patented high flow polyamide 6 resin (TechnylStar), reinforced with 35% of glass fibre, for injection moulding. Due to its outstanding flow characteristics, this grade provides a significant productivity improvement and allows more freedom in mould and part design versus a standard polyamide solutions.

General

Feature	Very high flow	Excellent surface finish
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Applications	Consumer good application Industrial Applications Power Tool & Garden Equipment PC / laptop / tablet	home & office furniture Outdoor Applications General Purpose
Colors available	Natural	Grey
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF35
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.41
Water absorption	24 hr, 23°C	ISO 62	%	0.9

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	10700 / 7400
Stress at break		ISO 527-1/-2	MPa	195 / 115
Strain at break		ISO 527-1/-2	%	3 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	10000 / 6200
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	295 / 195
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	75 / 80
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	13 / 19
Izod impact strength, +23°C	+23°C	ISO 180/1U	kJ/m ²	75 / 80
Izod notched impact strength, +23°C	+23°C	ISO 180/1A	kJ/m ²	13 / 16

TECHNICAL DATA SHEET

TECHNYL STAR S 216 V35 NC

	Condition	Standard	Unit	Value
Thermal properties				
Melting temperature, 10°C/min		ISO 11357-1	°C	222
Burning behaviour				
Flammability, 1.5 mm	1.5 mm	UL 94		HB
Flammability, 3.0 mm	3.0 mm	UL 94		HB
Glow-wire flammability index, GWFI, 1.5 mm	1.5 mm	IEC 60695-2-12	°C	650

*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 245 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.