

TECHNICAL DATA SHEET

THERMEC S 4150R40

PPS, 40% glass fiber reinforced, for injection moulding

General

Polymer type	PPS (Polyphenylene sulfide)		
Processing technology	Injection molding		
Certification	RoHS	EC 1907/2006 (REACH)	
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PPS-GF40		
-----------------------	----------	--	--

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.67
Coefficient of thermal expansion - Parallel to flow (2)	70 to 150°C	ISO 11359-2	ppm/°C	30
Coefficient of thermal expansion - Perpendicular to flow (2)	70 to 150°C	ISO 11359-2	ppm/°C	60

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	15000 / -
Stress at break	5 mm/min	ISO 527-1/-2	MPa	165 / -
Strain at break	5 mm/min	ISO 527-1/-2	%	2.5 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	8 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	280
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	265
Thermal conductivity, through plane		ASTM E1461	W/m.K	0.35
Thermal conductivity, in plane		ASTM E1461	W/m.K	0.3

Electrical properties

Volume resistivity		IEC 62631-3-1	ohm.m	1E+012
Surface resistivity		IEC 62631-3-1	ohm	1E+015

TECHNICAL DATA SHEET

THERMEC S 4150R40

Condition	Standard	Unit	Value
-----------	----------	------	-------

Burning behaviour


Flammability, 0.75 mm	0.75 mm	UL 94		V0
-----------------------	---------	-------	--	----

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
*: conditioned according to ISO 1110

Processing conditions

Drying temperature/time	130-150 °C / 4-6h
Recommended melt temperature	310 - 340 °C
Recommended mould temperature	140 - 170 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.



Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.