

EXPERIMENTAL DATASHEET

TECHNYL 4EARTH C2E 218 V45 BK H

(Previously ECONAMID FL 6G45H2 BK)

Polyamide 6, 45% glass fiber reinforced, for injection moulding, black

General

Polymer type	PA6 (Polyamide 6)
--------------	-------------------

Product identification

ISO 1043 abbreviation	PA-GF45
ISO 16396 designation	PA6,GF45(R100),M1,S14-140

Condition	Standard	Unit	Value
-----------	----------	------	-------

*Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for black products.
: conditioned according to ISO 1110

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.