

TECHNICAL DATA SHEET

TECHNYL C 116 S15 NC

(Previously DOMAMID 6LVB15 300 NC)

Polyamide 6, 15% glass beads, improved flowability, for injection moulding, natural color

General

Feature	Improved flowability		
Polymer type	PA6 (Polyamide 6)		
Processing technology	Injection molding		
Certification	RoHS	EC 1907/2006 (REACH)	
Colors available	Natural		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA6-GB15
ISO 16396 designation	PA6,GB15,M1,S12-030

Physical properties

		Condition	Standard	Unit	Value
Density			ISO 1183	g/cm³	1.23
Humidity absorption	T=23°C, 50% RH		ISO 62	%	2.6
Molding shrinkage, parallel			ISO 294-4, 2577	%	0.9 - 1.1
Molding shrinkage, normal			ISO 294-4, 2577	%	0.9 - 1.1
Melt volume-flow rate, MVR, 5.0 kg	275°C, 5kg		ISO 1133	cm³/10 min	190
Viscosity number	96% H2SO4		ISO 307	cm³/g	125

TECHNICAL DATA SHEET

TECHNYL C 116 S15 NC

	Condition	Standard	Unit	Value
Mechanical properties				dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3600 / 1050
Stress at break	5 mm/min	ISO 527-1/-2	MPa	70 / 20
Strain at break	5 mm/min	ISO 527-1/-2	%	10 / 150
Yield stress	5 mm/min	ISO 527-1/-2	MPa	75 / 40
Yield strain		ISO 527-1/-2	%	4 / 12
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	3100 / 900
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	105 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m²	19 / 180
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m²	20 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m²	3 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	221
Temp. of deflection under load, 0.45 MPa	0.45 MPa	ISO 75	°C	165
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	65

Burning behaviour

Burning rate, FMVSS, Thickness 1 mm		FMVSS 302		< 100 mm/min
-------------------------------------	--	-----------	--	--------------


Test run at 23°C if not differently specified, DAM state (dry as moulded).
*: conditioned according to ISO 1110

Processing conditions


Drying temperature/time	75-85°C / 2-4h (with dew point of dried air < -30 °C)
Recommended melt temperature	230 - 260 °C
Recommended mould temperature	80 - 100 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Stress-strain, dry



Stress-strain, conditioned



Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.