

TECHNICAL DATA SHEET

TECHNYL C 216 V45 BK 34N

TECHNYL C 216 V45 BK 34N is a polyamide 6, reinforced with 45% of glass fibre, for injection moulding. This grade has been optimized to have good impact strength, a nice surface aspect and being easy to paint.

General

Feature	High dimensional stability	High stiffness
Polymer type	PA6 (Polyamide 6)	
Processing technology	Injection molding	
Certification	RoHS	EC 1907/2006 (REACH)
Applications	Consumer good application	Sport
Colors available	Black	Natural
Forms	Pellets	

Product identification

ISO 1043 abbreviation	PA6-GF45
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.51
Water absorption	24 hr, 23°C	ISO 62	%	0.8
Molding shrinkage, parallel		ISO 294-4, 2577	%	0.3
Molding shrinkage, normal		ISO 294-4, 2577	%	0.65

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	14500 / 9300
Stress at break		ISO 527-1/-2	MPa	210 / 135
Strain at break		ISO 527-1/-2	%	3 / 6
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	13500 / 8000
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	340 / 170
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	90 / 100
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	13 / 20

TECHNICAL DATA SHEET

TECHNYL C 216 V45 BK 34N


Condition	Standard	Unit	Value
Thermal properties			
Melting temperature, 10°C/min	ISO 11357-1	°C	222
Temp. of deflection under load, 1.80 MPa	ISO 75	°C	210

*: conditioned according to ISO 1110


Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	235 - 240 °C
Middle temperature	240 - 250 °C
Front temperature	250 - 260 °C
Recommended mould temperature	60 - 90 °C

Stress-strain, dry



Stress-strain, conditioned



Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 /1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 /1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.