

TECHNICAL DATA SHEET

TECHNYL C 236 V35 BK Z

TECHNYL C 236 V35 BK Z is a polyamide 6 reinforced with 35% of glass fiber, with improved impact resistance, for injection moulding. This grade offer a high impact strength and good mechanical properties.

General

Feature	Impact resistant		
Polymer type	PA6 (Polyamide 6)		
Processing technology	Injection molding		
Certification	RoHS EC 1907/2006 (REACH)	UL-Yellow Card	
Applications	Consumer good application Wire & Cable	Industrial Applications	
Colors available	Black		
Forms	Pellets		

Product identification

ISO 1043 abbreviation	PA6-GF35
-----------------------	----------

Condition	Standard	Unit	Value
-----------	----------	------	-------

Physical properties

Density		ISO 1183	g/cm ³	1.41
Water absorption	24 hr, 23°C	ISO 62	%	0.9

Mechanical properties

dam / cond.*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	9700 / -
Stress at break		ISO 527-1/-2	MPa	160 / -
Strain at break		ISO 527-1/-2	%	3.6 / -
Flexural modulus, ISO 178	2 mm/min	ISO 178	MPa	8600 / -
Flexural strength, ISO 178	2 mm/min	ISO 178	MPa	243 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m ²	86 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	15 / -

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	222
-------------------------------	--	-------------	----	-----

TECHNICAL DATA SHEET

TECHNYL C 236 V35 BK Z

	Condition	Standard	Unit	Value
Burning behaviour				
UL Yellow Card availability 	Click here to have access to the UL Yellow Card → QMFZ2.E44716			
Flammability, 0.75 mm	0.75 mm	UL 94		HB

**: conditioned according to ISO 1110*

Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	230 - 235 °C
Middle temperature	235 - 240 °C
Front temperature	240 - 250 °C
Recommended mould temperature	60 - 90 °C

Injection notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

Injection advice

For reinforced polyamides, Domo recommends the use of steel with a high content of carbon, and purified for polishing, to avoid or limit the abrasion. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm) or X160CrMoV12 (EN Norm) - 1.2601 / 1.2379 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.