

### TECHNICAL DATA SHEET

## TECHNYL 4EARTH A1E 318 V25 BK H

(Previously TECHNYL 4EARTH A4E 318 V25 BLACK)

Polyamide 66, reinforced with 25% of glass fibers, heat stabilized and impact modified, for extrusion, black

### General

Feature	Heat-aging stabilized	Medium viscosity
Polymer type	PA66 (Polyamide 66)	
Processing technology	Extrusion	
Certification	RoHS	EC 1907/2006 (REACH)
Applications	General Purpose	
Colors available	Black	
Forms	Pellets	

### Product identification

ISO 1043 abbreviation	PA66(REC)-GF25
ISO 16396 designation	PA66,GF25(R100),EH,S14-080

Condition	Standard	Unit	Value
-----------	----------	------	-------

### Physical properties

Molding shrinkage, parallel		ISO 294-4, 2577	%	0.15
Molding shrinkage, normal		ISO 294-4, 2577	%	0.95

### Mechanical properties

dam / cond.\*

Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	8000 / -
Stress at break		ISO 527-1/-2	MPa	155 / -
Strain at break		ISO 527-1/-2	%	3.5 / -
Charpy impact strength, +23°C	+23°C	ISO 179/1eU	kJ/m <sup>2</sup>	75 / -
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m <sup>2</sup>	10 / -

\*: conditioned according to ISO 1110

### TECHNICAL DATA SHEET

### TECHNYL 4EARTH A1E 318 V25 BK H

#### Processing conditions

Drying temperature/time	80 °C
Suggested max moisture	0.2 %
Rear temperature	270 - 280 °C
Middle temperature	275 - 285 °C
Front temperature	280 - 290 °C
Recommended mould temperature	70 - 100 °C

#### Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.