

EXPERIMENTAL DATASHEET

TECHNYL A 208F2 NC

Polyamide 66, heat-aging stabilized, improved flowability, for injection molding, natural color

General

Polymer type	PA66 (Polyamide 66)
--------------	---------------------

Product identification

ISO 1043 abbreviation	PA66
ISO 16396 designation	PA66,M1H,S14-030

Physical properties	Condition	Standard	Unit	Value
Density		ISO 1183	g/cm ³	1.14

Mechanical properties	Condition	Standard	Unit	Value	dam / cond.*
Tensile modulus	1 mm/min	ISO 527-1/-2	MPa	3200 / -	
Stress at break		ISO 527-1/-2	MPa	68 / -	
Strain at break		ISO 527-1/-2	%	26 / -	
Yield stress		ISO 527-1/-2	MPa	90 / -	
Yield strain		ISO 527-1/-2	%	7 / -	
Charpy impact strength, -30°C	-30°C	ISO 179/1eU	kJ/m ²	69 / -	
Charpy notched impact strength, +23°C	+23°C	ISO 179/1eA	kJ/m ²	5.1 / -	
Charpy notched impact strength, -30°C	-30°C	ISO 179/1eA	kJ/m ²	3.8 / -	

Thermal properties

Melting temperature, 10°C/min		ISO 11357-1	°C	261
Temp. of deflection under load, 1.80 MPa	1.80 MPa	ISO 75	°C	70

Test run at 23°C if not differently specified, DAM state (dry as moulded), valid for natural colored products.
*: conditioned according to ISO 1110

EXPERIMENTAL DATASHEET

TECHNYL A 208F2 NC

Processing conditions

Drying temperature/time	80°C
Suggested max moisture	0.2 %
Rear temperature	260 - 270 °C
Middle temperature	270 - 280 °C
Front temperature	280 - 290 °C
Recommended mould temperature	60 - 80 °C

These parameters are typical of the product but should be related to the type of machinery used and to the type of moulded part.

Disclaimer

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufacturers in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.