

TECHNICAL DATA SHEET

TECHNYL PROTECT A 60G1 V25 GY 2622

TECHNYL PROTECT A 60G1 V25 GY 26223 is a polyamide 66 based on a non-halogenated flame retardant system, reinforced with 25% of glass fiber, heat stabilized, for injection molding. This grade offers excellent flame retardancy properties (UL 94, 5VA, GWIT) combined with excellent processing, mechanical and electrical performance.

General

|                       |                                    |                                                               |
|-----------------------|------------------------------------|---------------------------------------------------------------|
| Feature               | UL V0                              | Halogen and red phosphorus free flame retardant               |
| Polymer type          | PA66 (Polyamide 66)                |                                                               |
| Processing technology | Injection molding                  |                                                               |
| Certification         | RoHS<br>EC 1907/2006 (REACH)       | UL-Yellow Card<br>European Railways Certifications EN 45545-2 |
| Applications          | Electrical/Electronic Applications |                                                               |
| Colors available      | Black<br>Grey<br>White             | Natural<br>Blue                                               |
| Forms                 | Pellets                            |                                                               |

Product identification

|                       |                  |
|-----------------------|------------------|
| ISO 1043 abbreviation | PA66-GF25 FR(40) |
|-----------------------|------------------|

| Condition | Standard | Unit | Value |
|-----------|----------|------|-------|
|-----------|----------|------|-------|

Physical properties

|                              |                |          |                   |           |
|------------------------------|----------------|----------|-------------------|-----------|
| Density                      |                | ISO 1183 | g/cm <sup>3</sup> | 1.38      |
| Humidity absorption          | T=23°C, 50% RH | ISO 62   | %                 | 1.7 - 1.8 |
| Water absorption             | 24 hr, 23°C    | ISO 62   | %                 | 1.1 - 1.2 |
| Water absorption, saturation |                |          | %                 | 5.6       |

Mechanical properties

dam / cond.\*

|                               |          |              |                   |              |
|-------------------------------|----------|--------------|-------------------|--------------|
| Tensile modulus               | 1 mm/min | ISO 527-1/-2 | MPa               | 10000 / 7000 |
| Stress at break               |          | ISO 527-1/-2 | MPa               | 120 / 80     |
| Strain at break               |          | ISO 527-1/-2 | %                 | 1.8 / 2.4    |
| Flexural modulus, ISO 178     | 2 mm/min | ISO 178      | MPa               | 6300 / 4250  |
| Flexural strength, ISO 178    | 2 mm/min | ISO 178      | MPa               | 180 / 135    |
| Charpy impact strength, +23°C | +23°C    | ISO 179/1eU  | kJ/m <sup>2</sup> | 35 / 38      |

TECHNICAL DATA SHEET

TECHNYL PROTECT A 60G1 V25 GY 2622

|                                          | Condition    | Standard    | Unit | Value |
|------------------------------------------|--------------|-------------|------|-------|
| <b>Thermal properties</b>                |              |             |      |       |
| Melting temperature, 10°C/min            |              | ISO 11357-1 | °C   | 263   |
| Temp. of deflection under load, 0.45 MPa | 0.45 MPa     | ISO 75      | °C   | 259   |
| Temp. of deflection under load, 1.80 MPa | 1.80 MPa     | ISO 75      | °C   | 235   |
| Vicat softening temperature              | 50°C/h - 50N | ISO 306     | °C   | 245   |

**Electrical properties**

|                                |            |               |       |        |
|--------------------------------|------------|---------------|-------|--------|
| Volume resistivity             |            | IEC 62631-3-1 | ohm.m | 6E+012 |
| Surface resistivity            |            | IEC 62631-3-1 | ohm   | 2E+015 |
| Comparative tracking index     | Solution A | IEC 60112     | V     | 600    |
| CTI performance level category |            | Sol A         |       | PLC 0  |
| Dielectric strength            | 1 mm       | IEC 60243-1   | kV/mm | 35     |

**Burning behaviour**

|                                                                                                                |                                                                                 |                |    |      |
|----------------------------------------------------------------------------------------------------------------|---------------------------------------------------------------------------------|----------------|----|------|
| UL Yellow Card availability  | Click here to have access to the UL Yellow Card → <a href="#">YC A 60G1 V25</a> |                |    |      |
| Glow-wire flammability index, GWFI, 0.40 mm                                                                    | 0.40 mm                                                                         | IEC 60695-2-12 | °C | 960  |
| Glow-wire flammability index, GWFI, 0.75 mm                                                                    | 0.75 mm                                                                         | IEC 60695-2-12 | °C | 960  |
| Glow-wire flammability index, GWFI, 1.5 mm                                                                     | 1.5 mm                                                                          | IEC 60695-2-12 | °C | 960  |
| Glow-wire flammability index, GWFI, 3.0 mm                                                                     | 3.0 mm                                                                          | IEC 60695-2-12 | °C | 960  |
| Glow-wire ignition temperature, GWIT, 0.40 mm                                                                  | 0.40 mm                                                                         | IEC 60695-2-13 | °C | 750  |
| Glow-wire ignition temperature, GWIT, 0.75 mm                                                                  | 0.75 mm                                                                         | IEC 60695-2-13 | °C | 750  |
| Glow-wire ignition temperature, GWIT, 1.5 mm                                                                   | 1.5 mm                                                                          | IEC 60695-2-13 | °C | 775  |
| Glow-wire ignition temperature, GWIT, 3.0 mm                                                                   | 3.0 mm                                                                          | IEC 60695-2-13 | °C | 800  |
| Burning rate, FMVSS, Thickness 1 mm                                                                            |                                                                                 | FMVSS 302      |    | <100 |

\*: conditioned according to ISO 1110

TECHNICAL DATA SHEET

TECHNYL PROTECT A 60G1 V25 GY 2622

**Processing conditions**

|                               |              |
|-------------------------------|--------------|
| Suggested max moisture        | 0.15 %       |
| Rear temperature              | 265 - 275 °C |
| Middle temperature            | 265 - 275 °C |
| Front temperature             | 270 - 280 °C |
| Recommended mould temperature | 60 - 80 °C   |

**Injection notes**

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point minimum -20°C. Recommended time 2-4h.

**Injection advice**

All reinforced, flame retardant compounds generate some level of abrasion/corrosion to the steel processing equipment. These issues may be magnified by using incorrect processing conditions (temperatures, residence time, moisture level ...) during the moulding process. Therefore, Domo recommends you adhere to the processing conditions detailed in this technical data sheet. For equipment that comes into contact with molten flame retardant compounds, Domo advises you to use a steel with high chromium and high carbon content (having a minimum concentration of 16% chromium) to prevent corrosion and abrasion. For the correct reference of steel associated to flame retardant compounds' processing, please refer to your equipment manufacturers. In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered. The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

**Disclaimer**

The information provided in this documentation corresponds to our technical knowledge at the date of its publication and do not constitute a specification. This information may be subject to revision at our discretion. Domo cannot anticipate all conditions under which this information and our products of other manufactures in combination with our products may be used. Domo accepts no responsibility for results obtained by the application of this information or for the safety and suitability of our products alone or in combination with other products. Users are advised to make their own tests to determine the safety and suitability of each product or product combination for their own purposes. Unless otherwise agreed in writing, Domo sells the product without warranties. Buyers and users assume all responsibility and liability for loss or damage arising from handling and use of our products, whether used alone or in combination with other products. Unless specifically indicated, the grades mentioned are not suitable for applications in the pharmaceutical/medical sector.