

**PRL ABS-G5-(color)-3**Units 

Polymer Resources Ltd. - Acrylonitrile Butadiene Styrene

Action

Legend **General Information****General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 5.0% Filler by Weight
Additive	• UV Stabilizer
Features	• UV Resistant
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

**ASTM & ISO Properties <sup>1</sup>****Physical**

	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.08		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	0.50 to 5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	3.0E-3 to 5.0E-3	in/in	ASTM D955

**Mechanical**

	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength (Yield, 0.125 in)	6600	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	6200	psi	ASTM D638
Flexural Modulus (0.125 in)	420000	psi	ASTM D790
Flexural Strength (Break, 0.125 in)	9500	psi	ASTM D790

**Impact**

	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact (73°F, 0.125 in)	1.5	ft·lb/in	ASTM D256

**Thermal**

	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	200	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	190	°F	ASTM D648

**Processing Information****Injection**

	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	175 to 185	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	375 to 390	°F
Middle Temperature	410 to 430	°F
Front Temperature	410 to 440	°F
Processing (Melt) Temp	440 to 460	°F
Mold Temperature	120 to 140	°F

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.