



Wednesday, August 30, 2023

PRL NY66-GP1-(color)H

Polymer Resources Ltd. - Polyamide 66

Units English ▼

Action	Legend (Open)

General Information

General			
Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Heat Stabilizer	• Lubricant	
Features	• General Purpose	• Heat Stabilized	• Lubricated
RoHS Compliance	• RoHS Compliant		
UL File Number	• E113219		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.012 to 0.018	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 0.125 in)	12000	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	12000	psi	ASTM D638
Flexural Modulus (0.125 in)	450000	psi	ASTM D790
Flexural Strength (0.125 in)	17000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.0	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	445	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	190	°F	ASTM D648
RTI Elec			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	
RTI Imp			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	
RTI Str			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-2		
0.12 in	V-2		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	165 to 185	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	510 to 530	°F
Middle Temperature	520 to 540	°F
Front Temperature	530 to 550	°F
Processing (Melt) Temp	530 to 560	°F
Mold Temperature	150 to 200	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.