

PRL PC-BR1-(color)-5**Polymer Resources Ltd. - Polycarbonate**Units **Action****Legend (Open)****General Information****General**

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> North America 		
Features	<ul style="list-style-type: none"> Food Contact Acceptable Medium Heat Resistance 	<ul style="list-style-type: none"> Ultra High Impact Resistance Ultra High Viscosity 	
RoHS Compliance	<ul style="list-style-type: none"> RoHS Compliant 		
Forms	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Blow Molding 	<ul style="list-style-type: none"> Extrusion 	

ASTM & ISO Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.20		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	1.0 to 5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 8.0E-3	in/in	ASTM D955
Mechanical			
Tensile Strength (Yield, 0.125 in)	9000	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	9600	psi	ASTM D638
Tensile Elongation (Yield, 0.125 in)	7.0	%	ASTM D638
Tensile Elongation (Break, 0.125 in)	120	%	ASTM D638
Flexural Modulus (0.125 in)	335000	psi	ASTM D790
Flexural Strength (Break, 0.125 in)	13500	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	14	ft-lb/in	ASTM D256
Gardner Impact (0.125 in)	> 320	in-lb	ASTM D3029
Hardness			
Rockwell Hardness			ASTM D785
M-Scale	70		
R-Scale	118		
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	275	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	265	°F	ASTM D648
Vicat Softening Temperature	310	°F	ASTM D1525 ²
Optical			
Light Transmittance (100.0 mil)	88.0	%	ASTM D1003
Haze (100.0 mil)	1.00	%	ASTM D1003

Processing Information

	Nominal Value	Unit
Extrusion		
Drying Temperature	245 to 255	°F
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	570 to 610	°F
Cylinder Zone 2 Temp.	590 to 630	°F
Cylinder Zone 3 Temp.	610 to 650	°F
Melt Temperature	600 to 650	°F

Notes¹ Typical properties: these are not to be construed as specifications.² Rate B (120°C/h), Loading 2 (50 N)

The information contained herein is based on our knowledge and belief of current facts, existing publications and generally accepted good practice. It may not be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.