



Wednesday, August 30, 2023

PRL PC-FR3-D-(color)-3

Polymer Resources Ltd. - Polycarbonate

Units

English ▼

Action	Legend (Open)

General Information

General			
Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Flame Retardant	• UV Stabilizer	
Features	• Flame Retardant	• High Flow	• UV Resistant
RoHS Compliance	• RoHS Compliant		
UL File Number	• E113219		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	14 to 20	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Outdoor Suitability	f1		UL 746C
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 0.125 in)	9000	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	8000	psi	ASTM D638
Tensile Elongation (Yield, 0.125 in)	7.0	%	ASTM D638
Tensile Elongation (Break, 0.125 in)	90	%	ASTM D638
Flexural Modulus (0.125 in)	320000	psi	ASTM D790
Flexural Strength (0.125 in)	13000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	12	ft·lb/in	ASTM D256
Gardner Impact (0.125 in)	> 320	in·lb	ASTM D3029
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	70		
R-Scale	118		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	275	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	265	°F	ASTM D648
Vicat Softening Temperature	300	°F	ASTM D1525 ²
RTI Elec			UL 746B
0.06 in	257	°F	
0.12 in	257	°F	
RTI Imp			UL 746B
0.06 in	230	°F	
0.12 in	230	°F	
RTI Str			UL 746B
0.06 in	257	°F	
0.12 in	257	°F	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength (0.0591 in)	580	V/mil	ASTM D149
Arc Resistance (0.0591 in)	PLC 5		ASTM D495

Comparative Tracking Index (CTI) (0.0591 in)	PLC 2	UL 746A
High Amp Arc Ignition (HAI)		UL 746A
0.06 in	PLC 0	
0.12 in	PLC 0	
High Voltage Arc Tracking Rate (HVTR) (0.0591 in)	PLC 3	UL 746A
Hot-wire Ignition (HWI)		UL 746A
0.06 in	PLC 2	
0.12 in	PLC 2	
Flammability	Nominal Value	Unit Test Method
Flame Rating		UL 94
0.06 in	V-0	
0.12 in	V-0	
	5VA	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	245 to 255	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	510 to 550	°F
Middle Temperature	530 to 570	°F
Front Temperature	550 to 590	°F
Processing (Melt) Temp	540 to 590	°F
Mold Temperature	160 to 200	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

² Rate B (120°C/h), Loading 2 (50 N)

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.