

PRL PC-G40-(color)-1**Polymer Resources Ltd. - Polycarbonate**Units **Action****Legend (Open)****General Information****General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Additive	• Mold Release
Features	• Good Mold Release
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

ASTM & ISO Properties ¹**Physical**

	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.50		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	2.0 to 10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 3.0E-3	in/in	ASTM D955

Mechanical

	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 0.125 in)	24000	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	24000	psi	ASTM D638
Flexural Modulus (0.125 in)	1.40E+6	psi	ASTM D790
Flexural Strength (0.125 in)	27000	psi	ASTM D790

Impact

	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.5	ft·lb/in	ASTM D256

Thermal

	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	305	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	295	°F	ASTM D648

Processing Information**Injection**

	Nominal Value	Unit
Drying Temperature	245 to 255	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	560 to 600	°F
Middle Temperature	580 to 620	°F
Front Temperature	600 to 640	°F
Processing (Melt) Temp	575 to 625	°F
Mold Temperature	180 to 240	°F

Notes

¹ Typical properties: these are not to be construed as specifications.

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all statements and recommendations in conjunction with our conditions of sale, which apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.