

# Polymer Resources

Classic® Engineering Plastic Compounds

Wednesday, August 30, 2023

## PRL PC-IM4

### Polymer Resources Ltd. - Polycarbonate

Units English

Action

Legend (Open)



#### General Information

##### General

Material Status	• Commercial: Active	
Availability	• North America	
Additive	• Impact Modifier	
Features	• High Flow • High Impact Resistance	• Impact Modified • Low Temperature Impact Resistance
RoHS Compliance	• RoHS Compliant	
Forms	• Pellets	
Processing Method	• Injection Molding	

#### ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.19		ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20 to 30	g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 0.125 in)	7700	psi	ASTM D638
Tensile Strength (Break, 0.125 in)	7500	psi	ASTM D638
Tensile Elongation (Yield, 0.125 in)	6.0	%	ASTM D638
Tensile Elongation (Break, 0.125 in)	100	%	ASTM D638
Flexural Modulus (0.125 in)	290000	psi	ASTM D790
Flexural Strength (0.125 in)	10000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
0°F, 0.125 in	10	ft-lb/in	
73°F, 0.125 in	12	ft-lb/in	
Gardner Impact (0.125 in)	> 320	in-lb	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed, 0.125 in)	255	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed, 0.125 in)	245	°F	ASTM D648
Vicat Softening Temperature	285	°F	ASTM D1525 <sup>2</sup>

#### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	245 to 255	°F
Drying Time	3.0 to 4.0	hr
Drying Time, Maximum	8.0	hr
Rear Temperature	490 to 530	°F
Middle Temperature	510 to 550	°F
Front Temperature	530 to 570	°F
Processing (Melt) Temp	525 to 575	°F
Mold Temperature	160 to 200	°F

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Rate B (120°C/h), Loading 2 (50 N)

The information contained herein is based on our best knowledge and we believe it to be true and accurate. Please read all

statements and recommendations in conjunction with the technical data sheets apply to all goods sold by us. Statements concerning possible uses of materials described herein are not to be construed as recommendations for use of such materials in the infringement of any patent or copyright. Lot data is available upon request. The user of this material must make their own evaluations to determine the suitability of this material from a technical as well as health, safety and environmental standpoint. This data is not intended for specification purposes.