

DURANEX® PBT General Properties(ISO)

Item	Unit	Test Method	Film, Extrusion Molding
			700FP
			High Viscosity
Color No.			EF201R
ISO Marking Code		ISO11469 (JIS K6999)	>PBT<
Density	g/cm ³	ISO 1183	1.31
IV			1.14
Tm	°C		223
Tc	°C		170
ΔH	J/g		46
Tg	°C		35
Flammability		UL94	HB Equivalent
The yellow card File No.			
Appropriate List number of Ministerial Ordinance for Export Trade Control			Item 16 of Appendix -1

All figures in the table are the typical values of the material and not the minimum values of the material specifications. All data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application. For safe handling of materials we supply, it is advised to refer to the Material Safety Data Sheet "SDS" of the proper material. This brochure is edited based on reference literatures, information and data currently available to us. So the contents of this brochure are subject to change without notice due to new data.

Copyright Polyplastics Co., Ltd. All rights reserved.

