

Polyacetal (POM)

TEPCON®

M450 NAT

CF2001

Standard

POLYPLASTICS CO., LTD.



General Properties of M450 NAT

table1-1 General Properties (ISO)

Item	Unit	Test Method	Standard
			M450 NAT Super High Flow, Fast Molding Cycle
Color			CF2001
ISO(JIS)quality-of-the-material display:		ISO11469 (JIS K6999)	>POM<
Density	g/cm ³	ISO 1183	1.41
Water absorption (23°C,24hrs,1mmt)	%	ISO 62	0.5
MFR (190°C、 2.16kg)	g/10min	ISO 1133	45
MVR (190°C、 2.16kg)	cm ³ /10min	ISO 1133	38
Tensile strength	MPa	ISO 527-1,2	63
Strain at break	%	ISO 527-1,2	27 ¹
Flexural strength	MPa	ISO 178	89
Flexural modulus	MPa	ISO 178	2,550
Charpy notched impact strength (23°C)	kJ/m ²	ISO 179/1eA	5
Temperature of deflection under load (1.8MPa)	°C	ISO 75-1,2	100
Coefficient of linear thermal expansion (23 - 55°C、 Flow direction)	x10 ⁻⁵ /°C	Our standard	11
Coefficient of linear thermal expansion (23 - 55°C、 Transverse direction)	x10 ⁻⁵ /°C	Our standard	11
Electric strength (3mmt)	kV/mm	IEC 60243-1	19
Tracking resistance (CTI)	V	IEC 60112	(600)<
Rockwell hardness	M(Scale)	ISO2039-2	80
Flammability		UL94	HB
The yellow card File No.			E146187
Appropriate List number of Ministerial Ordinance for Export Trade Control			

*1) Nominal strain at break

All figures in the table are the typical values of the material and not the minimum values of the material specifications.



NOTES TO USERS

- All property values shown in this brochure are the typical values obtained under conditions prescribed by applicable standards and test methods.
- This brochure has been prepared based on our own experiences and laboratory test data, and therefore all data shown here are not always applicable to parts used under different conditions. We do not guarantee that these data are directly applicable to the application conditions of users and we ask each user to make his own decision on the application.
- It is the users' responsibility to investigate patent rights, service life and potentiality of applications introduced in this brochure. Materials we supply are not intended for the implant applications in the medical and dental fields, and therefore are not recommended for such uses.
- For all works done properly, it is advised to refer to appropriate technical catalogs for specific material processing.
- For safe handling of materials we supply, it is advised to refer to the Safety Data Sheet "SDS" of the proper material.
- This brochure is edited based on reference literature, information and data available to us at the time of creation. The contents of this brochure are subject to change without notice upon achievement of new data.
- Please contact our office for any questions about products we supply, descriptive literatures or any description in this brochure.

TEPCON® is a registered trademark of Polyplastics Taiwan Co., Ltd. in Taiwan and other countries.

POLYPLASTICS CO., LTD.

JR Shinagawa East Bldg.,
18-1, Konan 2-chome, Minato-ku, Tokyo, 108-8280 Japan
Tel: +81-3-6711-8610 Fax: +81-3-6711-8618

<http://www.polyplastics.com/en/>

(R190507-1856)

