



ROMIRA GMBH
Postfach 1964
Pinneberg, 25409 Germany



ROTEC ABS 1001 FR V0/5+
Acrylonitrile Butadiene Styrene (ABS), pellets

可燃性	值	测试方法
UL 阻燃等级		UL 94
1.5 mm, ALL	V-0	IEC 60695-11-10, -20
2.5 mm, ALL	V-0	
3.0 mm, ALL	V-0	
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
2.5 mm	PLC 1	
3.0 mm	PLC 1	
高电弧燃烧指数(HAI)		UL 746
2.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 1	UL 746
高电压电弧起痕速率 (HVTR)	PLC 2	UL 746
耐电弧性	PLC 7	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
1.5 mm	60.0 °C	
2.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI Imp		UL 746
1.5 mm	60.0 °C	
2.5 mm	60.0 °C	
3.0 mm	60.0 °C	
RTI		UL 746
1.5 mm	60.0 °C	
2.5 mm	60.0 °C	
3.0 mm	60.0 °C	

