

Technical Data Sheet

LURANYL® HT 220 E



PPE+PA Blend; extrusion and injection moulding grade; very high heat resistance

<i>Properties</i>	<i>Unit</i>	<i>Test Method</i>	<i>Test Conditions</i>	<i>Value*</i>	<i>Remarks</i>
<i>Mechanical</i>					
Tensile Modulus	MPa	ISO 527	23°C 1mm/min	2,100	
Tensile Strength	MPa	ISO 527	23°C 50 mm/min	50	
Elongation at Break	%	ISO 527	23°C 50 mm/min	25	
Impact Strength Notched (Charpy)	kJ/m ²	ISO 179/1eA	80 x 10 x 4 mm 23°C	6	
Impact Strength (Charpy)	kJ/m ²	ISO 179/1eU	80 x 10 x 4 mm 23°C	n.b.	
<i>Physical</i>					
Density	g/cm ³	ISO 1183	23°C, 50% RH	1.06	
<i>Thermal</i>					
Vicat Softening Temperature (B 50)	°C	ISO 306	50°C/h 50N	220	
Melt Volume Rate MVR	cm ³ /10 min	ISO 1133	275°C 5 kg	8	
Flammability (own test)	Class	UL 94	1.6 mm	HB	

* = Average figures which could vary with each production batch due to addition of pigments, antistatic agents, slip agents, light stabilizers or other additives.

The information submitted is based on our current knowledge and experience. In view of the many factors that may affect processing and application, these data do not relieve processors from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

