

SPECIFICATION

ITEM	METHOD	Condition	Unit	PG-383D
MFR 流動指數	ISO 1133	200°C*5kg	ml/10 min	2.5
SP 軟化點	ISO 306	1Kg,50°C/Hr	°C	106
TSy 引張強度	ISO 527	50 mm/min	M Pa	54
EL 延伸率	ISO 527	50 mm/min	%	6
FM 彎曲彈性率	ISO 178	2 mm/min	G Pa	82
FS 彎曲強度	ISO 178	2 mm/min	M Pa	82
透光率	—	—	—	89%
折射率	—	—	—	1.587
粒子YI	ASTM E-308	-	-	-2.00

* Physical properties by Analysis Department of Chimei Corp.

