



Component - Plastics

File Number: E56070

CHI MEI CORPORATION

59-1 SAN CHIA

JEN TE

TAINAN, 717 Taiwan



WONDERLITE: PC-616LS(a)

Polycarbonate (PC)

(a) - Ball pressure temperature is in accordance with IEC 60695-10-2 Method B.

Flammability	Value	Test Method
Flame Rating		UL 94
1.0 mm, ALL	V-0	IEC 60695-11-10, -20
1.5 mm, ALL	V-0	
2.0 mm, ALL	V-0, 5VB	
2.5 mm, ALL	V-0, 5VA	
3.0 mm, ALL	V-0, 5VA	
Glow Wire Flammability Index		IEC 60695-2-12
1.0 mm	930 °C	
1.5 mm	960 °C	
3.0 mm	960 °C	
Glow Wire Ignition Temperature		IEC 60695-2-13
1.0 mm	850 °C	
1.5 mm	875 °C	
3.0 mm	875 °C	
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746A
1.0 mm	PLC 3	
1.5 mm	PLC 3	
2.0 mm	PLC 2	
2.5 mm	PLC 2	
3.0 mm	PLC 0	
High Amp Arc Ignition (HAI)		UL 746A
1.0 mm	PLC 1	
1.5 mm	PLC 1	
2.0 mm	PLC 0	
2.5 mm	PLC 0	
3.0 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 2	UL 746A
Dielectric Strength	31 kV/mm	ASTM D149
Volume Resistivity	1.0E+14 ohms·cm	ASTM D257 IEC 60093
Thermal	Value	Test Method
RTI Elec		UL 746B
1.0 mm	130 °C	
1.5 mm	130 °C	
2.0 mm	130 °C	
2.5 mm	130 °C	
3.0 mm	130 °C	

Component - Plastics

File Number: E56070



Thermal	Value	Test Method
RTI Imp		UL 746B
1.0 mm	120 °C	
1.5 mm	120 °C	
2.0 mm	120 °C	
2.5 mm	120 °C	
3.0 mm	120 °C	
RTI Str		UL 746B
1.0 mm	130 °C	
1.5 mm	130 °C	
2.0 mm	130 °C	
2.5 mm	130 °C	
3.0 mm	130 °C	
Ball Pressure Test (135°C)	Pass	IEC 60695-10-2
Physical	Value	Test Method
Dimensional Change	0.0 %	ASTM D1042 ISO 2796

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-devices and appliances, where the acceptability of the combination is determined by UL.

