

General PMMA ACRYREX® Characteristics CM-207

特性 PROPERTIES	測試方法 ASTM TEST METHOD	測試條件 TEST CONDITION	單位 UNIT	一般級 GENERAL
				CM-207
熔融指數 Melt Flow Index	D1238	230 °C, 3.8 Kg	g/10 min	8.0
比重 Mass Density	D792	23 °C	-	1.19
假比重 Bulk Density	D1182		g/cm ³	0.7
吸水率 Water Absorption	D570		%	0.3
成型收縮率 Mould Shrinkage	D955		%	0.2~0.6
硬度 Hardness	D785	-	M Scale	88
折射率 Refractive Index	D542			1.491
全光透過率 Light Transmission	D1003		%	92
拉伸強度 (斷裂) Tensile Strength (Break)	D638	6 mm/min	Kg/cm ²	700
			lb/in ²	9900
延伸率 Tensile Elongation	D638	6 mm/min	%	7
彎曲強度 Flexural Strength	D790	2.8 mm/min	Kg/cm ²	1100
			lb/in ²	15600
IZOD 衝擊強度 Izod Impact Strength	D256 (Notched)	6.4 mm, 23°C	Kg-cm/cm	2.0
			ft-lb/in	0.37
維氏軟化溫度 Vicat Softening Temp.	D1525	1 Kg, 50 °C/hr	°C	107
			°F	225
熱變形溫度 Heat Distortion Temp.	D648	Unannealed	°C	95
			°F	203
UL 燃燒等級 UL Flammability	UL 94	-	-	1.5 mm HB

July 1, 2021

Notes : These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

The above statement is based on our current level of knowledge and covers the above products directly manufactured and supplied by CHI MEI CORPORATION at the date of issue. CHI MEI CORPORATION makes no warranties, whether express or implied, and assumes no liability in connection with any use of above information. Notwithstanding the foregoing, CHI MEI CORPORATION shall in no event be held obligated or liable for any claims due to or arising from (i) any customer provided, consigned, materials and/or parts, which are incorporated or adopted in the products; (ii) any combination of the products with material not provided or authorized by our company; (iii) any modifications to the products which are made or directed by customer; (iv) our compliance with the specifications, instructions, and/or designs provided by customer; (v) any anti-trust, unfair competition and/or other unlawful actions effected by customer; or (vi) any defects, infringement, breach and/or litigation which are arising out of customer's faults or otherwise not solely and directly attributable to CHI MEI CORPORATION. In no event shall CHI MEI CORPORATION be liable for any indirect, special, exemplary, punitive, or consequential damages (including lost profits) of any nature whatsoever arising out of the purchase, shipment, unloading, handling, or use of any product or otherwise.