

## Globalene TPV 1473A NT MD PRODUCT DATA SHEET

A medium-high hardness, multi-purpose thermoplastic elastomer featuring excellent compression set and high temperature performance. Globalene TPV 1473A NT MD can be used as a base material for compounding or processed by extrusion or molding for applications such as seals, window gaskets, other soft touch articles, tubing and plumbing applications in contact with water.

1473A NT MD certified by NSF to **NSF/ANSI Standard 61**-Drinking water system components-Health effects.

### Attributes:

- Globalene TPV is a fully vulcanized Thermoplastic Elastomers containing EPDM and PP.
- It is designed for applications requiring long term sealing performance at elevated temperatures.
- Suitable for injection molding, profile extrusion or re-compounding for plastics modification.
- Conventional thermoplastic processing equipment can be used.

### Applications:

Globalene TPV has quality sealing property, good chemical and weathering resistance and electrical property that is suitable to replace main stream TPV, thermoset EPDM rubber, Styrene based TPEs, flexible PVC and other TPEs. It is an excellent choice for applications requiring flexibility in the following markets: automotive parts, appliance, business machines, construction, consumer products, and electronics.

Property	Typical Value	Unit	Test Method
<b>PHYSICAL</b>			
Hardness:			
Injection Molded, 15 sec	87.5	Shore A	ISO 868
Specific Gravity			
23°C	0.96	N/A	ISO 1183
<b>MECHANICAL</b>			
Tensile Stress @ Break			
23°C, 500 mm/min	9.7	MPa	ISO 37
Tensile Stress @ 100%			
23°C, 500 mm/min	4.0	MPa	ISO 37
Tensile Strain @ Break			
23°C, 500 mm/min	600	%	ISO 37



## PROCESSING & HANDLING GUIDE

Globalene TPV 1000 series is a Polypropylene-EPDM based elastomer, which can be processed on conventional thermoplastic equipment by injection molding and extrusion. This product has a wide processing window in most applications with melt temperatures ranged from 180°C to 220°C. Pre-drying is recommended for 3-4 hours at 80-90°C before processing.

### INJECTION MOLDING CONDITIONS

Melt Temperature	200-220°C
Barrel Temperatures - Rear	180-190°C
Middle	200-220°C
Front	200-220°C
Nozzle	200-220°C
Injection Pressure	: 700-1000 psi (4.8-6.9 MPa)
Holding Pressure	: 300-600 psi (2.1-4.1 MPa)
Holding Time	: 4-10 seconds
Cooling Time	: 15-30 seconds
Mold Temperature	30-55°C
Screw Speed	100-200 RPM
Vent Depth	0.001 inch
Back Pressure	10-150 psi

### EXTRUSION CONDITIONS

Melt Temperature	180-220°C
Barrel Temperatures - Zone 1 (Feed)	180°C
Zone 2	190°C
Zone 3 (Transition)	200°C
Zone 4 (Metering)	210°C
Zone 5 (Front)	210°C
Die	210-220°C
Roll Temperature	20-50°C
Screen Pack	20 to 60 mesh
Screw	General Purpose 3:1 Compression ratio ≥ 24:1 L/D ratio

### Purging

Recommended to purge thoroughly before and after use of this product with fractional MFR polypropylene.

### Recycling & Regrinding

This product can be reprocessed with physical properties not degraded in general. Dry regrind prior to reprocessing required.

### Coloring

The use of polyolefin (PP or PE) based color concentrates is recommended when require for Natural TPV grades only. Apply back pressure in injection molding to disperse color.

### Storage & Handling

Globalene TPV is available in 25 kgs with Laminated aluminum foil bags (up to 750 kgs per pallet).

It has a storage life of 3 years from production date with proper storage at normal temperature away from direct sunlight.

Please refer to the Material Safety Data Sheet for this material prior to first time handling or contact LCY representative for further information.

### Disclaimer

The values quoted here are typical of the grade and obtained from LCY lab. However, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process. We hope above information is sufficient. Because of possible changes in the law and in the regulations, we recommend that customers continuing to use our products verify status every year from this date. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for the results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Before using a LCY product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LCY product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LCY except in writing signed by an authorized LCY employee. In no event shall LCY be liable for special, consequential, incidental, punitive, or exemplary damages.

