



组件 - 塑料
UL 档案号: E85783

LCY CHEMICAL CORP

3 Zhonglin Rd
Xiaogang District
Kaohsiung, 812 Taiwan



Globalene: 73F4-2(@)

Polypropylene (PP), pellets, mineral reinforced

(@) - May be followed by the letter C.

可燃性	值	测试方法
UL 阻燃等级		
1.5 mm, NC	HB	UL 94
3.0 mm, NC	HB	UL 94
3.0 mm, NC	HB40	IEC 60695-11-10, -20
1.5 mm, NC	HB75	IEC 60695-11-10, -20
电气性能	值	测试方法
热丝引燃 (HWI)		UL 746
1.5 mm	PLC 3	
3.0 mm	PLC 0	
高电弧燃烧指数(HAI)		UL 746
1.5 mm	PLC 0	
3.0 mm	PLC 0	
相比耐漏电起痕指数(CTI)	PLC 0	UL 746
介电强度	56 kV/mm	ASTM D149 IEC 60243-1
高电压电弧起痕速率 (HVTR)	PLC 0	UL 746
体积电阻率	1.0E+14 ohms·cm	ASTM D257 IEC 60093
耐电弧性	PLC 5	ASTM D495
热性能	值	测试方法
RTI Elec		UL 746
1.0 mm	115 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
RTI Imp		UL 746
1.0 mm	115 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
RTI		UL 746
1.0 mm	115 °C	
1.5 mm	115 °C	
3.0 mm	115 °C	
物理性能	值	测试方法
Dimensional Stability	0.0 %	ASTM D1042 ISO 2796

