

**Globalene 7533**

**Polypropylene Impact Copolymer 聚丙烯耐衝擊共聚物**

**Features 特性:**

- Good moldability 成形性佳
- Excellent long term heat aging 長期熱安定性優
- Good low temperature impact resistance 低溫耐衝擊性佳

**Typical Application 一般應用:**

- Injection:
  - Automotive part 汽機車配件
  - Appliances 電器產品
  - Furniture 傢俱
  - Crates 板條箱
  - Battery case 電池盒

Typical Properties	Test Method	Unit	Value
一般性質	測試方法	單位	數值
Melt flow rate (230°C, 2.16kg) 熔融流率	ASTM D1238	g/10min	5.0
Density 密度	ASTM D792	g/cm <sup>3</sup>	0.896
Tensile strength at yield 降伏點抗張強度	ASTM D638	kg/cm <sup>2</sup>	270
Elongation at yield 降伏點伸張率	ASTM D638	%	6
Flexural modulus 彎曲彈性係數	ASTM D790	kg/cm <sup>2</sup>	14600
Rockwell hardness 洛氏硬度	ASTM D785	R scale	84
Heat deflection temperature 熱變形溫度	ASTM D648	°C	95
Izod impact strength, notched 23°C / unnotched -18°C 艾氏衝擊強度, 切口 23°C / 無切口 -18°C	ASTM D256	kg-cm/cm	12/101
Drop Weight Impact strength, texture up, -29°C 落球衝擊強度	LCY	ft-lb	22
Mold shrinkage 收縮率	ASTM D955	%	1.4

**Storage and Handling 儲放與處置**

The inspected and qualified PP pellets will have a shelf life of minimum two years which is estimated from production date, if it is stored at LCY's best condition of proper temperature below 40°C, adequate humidity below 80%, complete package and indoor warehouse with specific protection from damage. However customers might not fully follow the recommendation to conduct the optimal storage condition, the shelf life is recommended six months only at customer site as received.

本公司所生產聚丙烯(塑膠粒)經首次產品驗證程序確認品質後，在適合的溫度(低於 40°C)、適當的濕度(低於 80%)、包裝袋完整、且具有防護設備的倉庫儲存下，其有效使用期限至少 2 年(以製造日期起算)。考量客戶端的儲存條件可能無法完全依照本公司建議來執行，客戶在購入聚丙烯產品(塑膠粒)後，保存期限建議最高為 6 個月。

**Disclaimer 免責聲明**

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。