

**Globalene ST868M Polypropylene Random copolymer 聚丙烯無規共聚物**

<p><b>Features 特性:</b></p> <ul style="list-style-type: none"> <li>• Excellent transparency 超高透明性</li> <li>• Good low temperature impact resistance 低溫耐衝擊性佳</li> </ul>	<p><b>Typical Application 一般應用:</b></p> <ul style="list-style-type: none"> <li>• Injection: <ul style="list-style-type: none"> <li>CD case CD 盒</li> <li>Appliances 家電</li> </ul> </li> <li>• ISBM: <ul style="list-style-type: none"> <li>Bottle 射吹瓶</li> </ul> </li> </ul>		
<b>Typical Properties</b>	<b>Test Method</b>	<b>Unit</b>	<b>Value</b>
一般性質	測試方法	單位	數值
Melt flow rate (230°C, 2.16kg) 熔融流率	ASTM D1238	g/10min	18
Density 密度	ASTM D792	g/cm <sup>3</sup>	0.899
Tensile strength at yield 降伏點抗張強度	ASTM D638	kg/cm <sup>2</sup>	290
Elongation at yield 降伏點伸張率	ASTM D638	%	12
Flexural modulus 彎曲彈性係數	ASTM D790	kg/cm <sup>2</sup>	11000
Rockwell hardness 洛氏硬度	ASTM D785	R scale	85
Heat deflection temperature 熱變形溫度	ASTM D648	°C	88
Izod impact strength,notched, 23°C 艾氏衝擊強度, 切口 23°C	ASTM D256	kg-cm/cm	3.8
Drop Weight Impact strength, texture up, 23°C/-29°C 落球衝擊強度	LCY	ft-lb	15/ -
Mold shrinkage 收縮率	ASTM D955	%	1.3

**Product Stewardship Information 產品責任資訊**

<p><b>a. Food approval 食品認可</b></p> <p>The base resin in Globalene ST868M is as specified in the Code of Federal Regulations, Title 21 CFR177.1520(a)(3)(i) and (c)3.1a. All the ingredients used in Globalene ST868M meet the respective FDA regulations and 21 CFR 177.1520(b) for use in direct contact with food.</p> <p>福聚烯 ST868M 樹脂符合美國食品及藥物管理局 21 CFR 177.1520(a)(3)(i)與(c)3.1a 之規範，且所有添加成份亦符合各自章節與 CFR 177.1520(b) 之規定，可直接與食物接觸</p>	
<p><b>b. Chemical Inventories 化學品庫</b></p> <p>All ingredients in Globalene ST868M are in compliance with the following chemical inventories:</p> <p>福聚烯 ST868M 之所有成份均登記於下列化學品庫中:</p> <p>(1)TSCA (U.S.A) (2) DSL (Canada)</p>	<p><b>c. UL certification 美國 UL 認證</b></p> <p>Globalene ST868M is certificate with UL 94HB, UL file no.: E85783</p> <p>福聚烯 ST868M 通過美國 UL 94HB 認證, UL 檔案編號: E85783</p>
<p>The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.</p> <p>以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。</p>	



總公司 · 台北市八德路四段 85 號 3 樓  
3F, 85, Sec. 4, Bade Road, Taipei 105,  
Taiwan, ROC  
Tel . 886-2-25288895 Fax . 886-2-25288823

工廠 · 高雄市大社區三奶里經建路 2 號  
No. 2, Jingjian Road, Sannai Village, Dashe Distri  
Kaohsiung City 81567, Taiwan, ROC  
Tel . 886-7-3513211 Fax . 886-7-3515424

