

Globalprene 1475F

Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚合物

<b>Features 特性:</b>		<b>Typical Application 一般應用:</b>			
• Oil-extended radial block copolymer	油展星型嵌段共聚合物	• Footwear compounding	鞋底加工		
• High strength and low viscosity	高強度及低黏度	• Plastics modification	塑料改質		
• High tensile strength	高引張強度				
• Reprocess able	可回收再加工				
<b>Typical Properties</b>		<b>Test Method</b>	<b>Unit</b>	<b>Typical Value</b>	<b>Range</b>
一般性質		測試方法	單位	數值	範圍
SM Content 苯乙烯含量		ASTM D5775	%	40	38~42
Specific Gravity 比重		ASTM D792	g/cc	0.91	N/A
Volatile Matter 揮發份		ASTM D5668	%	0.25	≤0.5
Ash Content 灰份		ASTM D5667	%	0.2	≤1.0
Oil Content 油份		ASTM D5774	wt%	33.3	31~36
Melt Flow Index (190°C, 5kg) 熔融流動指數		ASTM D1238	g/10min	5	3~6.3
Hardness 硬度		ASTM D2240	Shore A	63	62~68

Packing 包裝： 20kg paper bag 20 公斤紙袋

600kg super bag 600 公斤太空袋

All ingredients in the product are in compliance with the following chemical inventories:

United States: Toxics Substances Control Act Inventory (TSCA)

Europe: European Inventory of Existing Chemical Substances (EINECS)

Canada: Canadian Domestic/ Non-Domestic Substances List (DSL)

Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

Australia: Australian Inventory of Chemical Substances

Korea: Korean Existing Chemicals List (KECL)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

EU Directive 2002/95/EC RoHS (Restriction of certain Hazardous Substances)

EC No 1907/2006 SVHC (Substances of Very High Concern)

CEN Standard EN71.3

**Product Stewardship Information 產品責任資訊**

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

Head office 總公司 台北市八德路四段 83 號 3 樓  
3F, No.83, Sec. 4, Bade Road, Taipei 105, Taiwan

Tel : 886-2-2763-1611  
Fax : 886-2-27645749

USA office 美國 4903 Decker Drive Baytown, Texas 77520, USA

Tel : 1-281-424-6100  
Fax : 1-281-424-6169

China office 中國 廣東省惠州市大亞灣經濟技術發展區石化大道中 299 號  
299 Shihua Dadaozhong, Dayawan Economic and Technological  
Development Zone, Huizhou, Guangdong, China 516082

Tel : 86-752-5599000  
Fax : 86-752-5599000