

GLOBALPRENE 1546

Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚物

Features 特性 : <ul style="list-style-type: none"> Oil-extended linear block copolymer 油展線型嵌段共聚物 High strength and low viscosity 高强度及低黏度 Reprocess able 可回收再加工 		Typical Application 一般应用 : <ul style="list-style-type: none"> Footwear compounding 鞋底加工 Plastic Modification 塑料改质 Adhesives 黏着剂 Mechanical Parts 机械零件 			
Typical Properties : 一般性质		Test Method 测试方法	Unit 单位	Value 数值	Range 范围
SM Content 苯乙烯含量		ASTM D5775	%	40	38~42
Specific Gravity 比重		ASTM D792	g/cc	0.95	N/A
Volatile Matter 挥发份		ASTM D5668	%	0.1	≤0.2
Ash Content 灰份		ASTM D5667	%	0.1	≤1.0
Oil content 油份		ASTM D5774	wt%	25	20 ~ 30
Melt Flow Index (190°C, 5kg) 熔融流动指数		ASTM D1238	g/10min	> 50	> 50
Hardness 硬度		ASTM D2240	shore A	55	53 ~ 57

Packing 包装: 20 kg paper bag 20 公斤 纸袋
600 kg Super bag 600 公斤 太空包

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

Product Stewardship Information 产品责任信息

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各项数据为实验参考值，唯因使用时加工条件及环境之不同，而产生之差异非本公司所能保证与控制。

