

GLOBALPRENE 3545

Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚物

Features 特性 : <ul style="list-style-type: none"> • Linear structure 線型結構 • High diblock content 高雙嵌段 • Reprocess able 可回收再加工 		Typical Application 一般應用 : <ul style="list-style-type: none"> • Transparent shoe sole 透明鞋底 • Plastic modification 塑料改質 • Mechanical parts 機械零件 • Compounding for modification 混煉改質 • Adhesive 黏著劑 			
Typical Properties : 一般性質		Test Method 測試方法	Unit 單位	Value 數值	Range 範圍
SM Content 苯乙烯含量		ASTM D5775	%	45	43 ~ 47
Specific Gravity 比重		ASTM D792	g/cc	0.94	N/A
Volatile Matter 揮發份		ASTM D5668	%	0.3	≤ 0.5
Ash Content 灰份		ASTM D5667	%	0.2	≤ 1.0
Melt Flow Index(190 · 5kg)熔融流動指數		ASTM D1238	g/10min	55	40 ~ 70
Hardness 硬度		ASTM D2240	shore A	84	84 ~ 88
Diblock content 雙嵌段含量		LCY	%	63	60 ~ 66

Packing 包裝: 20 kg paper bag 20 公斤 紙袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

