

## Globalprene 3411

## Styrene-Butadiene block copolymer 苯乙烯-丁二烯嵌段共聚物

Features 特性 :		Typical Application 一般應用 :			
• Radial block copolymer	星型嵌段共聚物	• Asphalt modification	瀝青改質		
• High strength and high viscosity	高強度及高黏度	• Compounding for modification	混煉改質		
• High rebound	高回復性	• Adhesive	黏著劑		
Typical Properties :		Test Method	Unit	Value	Range
一般性質		測試方法	單位	數值	範圍
SM Content 苯乙烯含量		ASTM D5775	%	30	29.5~32.5
Specific Gravity 比重		ASTM D792	g/cc	0.94	N/A
Volatile Matter 揮發份		ASTM D5668	%	0.25	≤0.5
Ash Content 灰份		ASTM D5667	%	0.3	<1.0
Molecular Weight 分子量		ASTM D5296	Daltons	240k	235k~255k

Packing 包裝: 12、15 kg paper bag      12、15      公斤 紙袋  
400、450、408.2 kg super bag      400、450、408.2 公斤 太空袋

All ingredients in the products are in compliance with the following chemical inventories :

- United States: Toxics Substances Control Act Inventory (TSCA)
- Canada: Domestic Substances List (DSL) or Non-Domestic Substances List (NDSL)
- Europe: EINECS/ELINCS replaced by REACH
- Australia: Australian Inventory of Chemical Substances (AICS)
- New Zealand: New Zealand Inventory of Chemicals (NZIoC)
- Korea: Korean Existing Chemicals List (KECL)
- Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)
- The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)
- China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)
- Taiwan: Existing Chemical Substances Inventory (ECSI)

### Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.  
以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

