

GLOBALPRENE 7533 Styrene-Ethylene/Butylene block copolymer 苯乙烯-乙烯/丁烯嵌段共聚物

Features 特性 :		Typical Application 一般應用 :			
• Linear block copolymer	線狀嵌段共聚物	• Plastic modification	塑料改質		
• Excellent weather and heat resistance	優良的耐候性及耐熱性	• Adhesives	黏著劑		
• High mechanical strength	高機械強度	• Compounding for modification	混鍊改質		
• High compression set	高壓縮永久變形	• Toys	玩具		
• Good compatibility with plastics	與塑膠有好的相容性	• Asphalt modification	瀝青改質		
Typical Properties :	Test Method	Unit	Value	Range	
一般性質	測試方法	單位	數值	範圍	
SM Content 苯乙烯含量	ASTM D5775	%	31.5	30 ~ 33	
Specific Gravity 比重	ASTM D792	g/cc	0.91	≥ 0.91	
Volatile Matter 揮發份	ASTM D5668	%	0.2	≤ 0.5	
Ash Content 灰份	ASTM D5667	%	0.6	≤ 1.0	
5wt% / 25°C Toluene Viscosity 5wt% / 25°C 甲苯黏度	ASTM D2196	cP	400	250 ~ 550	

Note : SM content is measured on polymer before hydrogenation. 苯乙烯含量為氫化前測量值

Packing 包裝: 13kg PE 袋 13 公斤 PE 袋

All ingredients in the products are in compliance with the following chemical inventories:

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

