

GLOBALPRENE 5516D Styrene-Isoprene block copolymer 苯乙烯-異戊二烯嵌段共聚合物

Features 特性：

- Linear block copolymer 線狀嵌段共聚合物
- Low strength and low viscosity 低強度及低黏度
- Triblock and diblock copolymer 三嵌段及雙嵌段共聚合物

Typical Application 一般應用：

- Hot melt adhesive 熱熔膠
- Solvent base adhesive 溶劑膠

Typical Properties：

一般性質

Test Method	Unit	Value	Range
測試方法	單位	數值	範圍
ASTM D5775	%	16	15 ~ 17
ASTM D5296	%	25	< 30
ASTM D792	g/cc	0.93	N/A
ASTM D5668	%	0.14	≤ 0.5
ASTM D5667	%	0.1	≤ 0.5
ASTM D1238	g/10min	9	6 ~ 12
ASTM D2196	cP	1,000	800 ~ 1,200

Packing 包裝： 25 kg paper bag 25 公斤 紙袋
600 kg、1000 kg super sack 600 公斤、1000 公斤 太空包

All ingredients in the products are in compliance with the following chemical inventories：

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.
以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

