

GLOBALPRENE 5517 Styrene-Isoprene block copolymer 苯乙烯-異戊二烯嵌段共聚合物

Typical Properties :	Test Method	Unit	Value	Range
一般性質	測試方法	單位	數值	範圍
SM Content 苯乙烯含量	ASTM D5775	%	15	13 ~ 17
Diblock 雙嵌段	ASTM D5296	%	38	35 ~ 40
Specific Gravity 比重	ASTM D792	g/cc	0.93	N/A
Volatile Matter 揮發份	ASTM D5668	%	0.25	≤ 0.5
Ash Content 灰份	ASTM D5667	%	0.7	≤ 1.0
Melt Flow Index (190°C, 5kg) 熔融流動指數	ASTM D1238	g/10min	20	15 ~ 25
25wt% / 25°C Toluene Viscosity 25wt% / 25°C 甲苯黏度	ASTM D2196	cP	800	650 ~ 950

Packing 包裝 : 20 kg paper bag 20 公斤 紙袋
600 kg super bag 600 公斤 太空包

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECIS)

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.
以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

