

**GLOBALPRENE 5562U Styrene-Isoprene block copolymer 苯乙烯-異戊二烯嵌段共聚合物**

<b>Features 特性 :</b> • Linear block copolymer • High SM content	線狀嵌段共聚合物 高苯乙烯含量	<b>Typical Application 一般應用:</b> • Hot melt adhesive • Solvent base adhesive	熱熔膠 溶劑膠	
<b>Typical Properties :</b> 一般性質	<b>Test Method</b> 測試方法	<b>Unit</b> 單位	<b>Value</b> 數值	<b>Range</b> 範圍
SM Content 苯乙烯含量	ASTM D5775	%	45	43 ~ 47
Specific Gravity 比重	ASTM D792	g/cc	0.93	N/A
Volatile Matter 揮發份	ASTM D5668	%	0.25	≤ 0.5
Ash Content 灰份	ASTM D5667	%	0.05	< 0.1
Melt Flow Index (200°C, 5kg) 熔融流動指數	ASTM D1238	g/10min	40	35 ~ 45

Packing 包裝: 20 kg paper bag 20 公斤 紙袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

**This product pass through the tests of Skins Sensitization, Skin irritation and cytotoxicity.**

**Product Stewardship Information 產品責任資訊**

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項資料為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

