

GLOBALPRENE 5614 Styrene-Isoprene block copolymer 苯乙烯-異戊二烯嵌段共聚合物

Features 特性 :		Typical Application 一般應用:			
• Hybrid block copolymer	混合嵌段共聚合物	• Hot melt adhesive	熱熔膠		
• Low strength and low viscosity	低強度及低黏度	• Solvent base adhesive	溶劑膠		
Typical Properties :		Test Method	Unit	Value	Range
一般性質		測試方法	單位	數值	範圍
SM Content 苯乙烯含量		ASTM D5775	%	14	13 ~ 15
Diblock 雙嵌段		ASTM D5296	%	12	10 ~ 14
Volatile Matter 揮發份		ASTM D5668	%	0.14	≤ 0.5
Ash Content 灰份		ASTM D5667	%	1.0	0.7 ~ 1.3
Melt Flow Index (190°C, 5kg) 熔融流動指數		ASTM D1238	g/10min	9	6 ~ 12
25wt% Toluene Viscosity 25%甲苯黏度		ASTM D2196	cP	1400	850 ~ 2050

Packing 包裝: 20 kg paper bag 20 公斤 紙袋

All ingredients in the products are in compliance with the following chemical inventories :

United States: Toxics Substances Control Act Inventory (TSCA)

Canada: Domestic Substances List (DSL)

Europe: EINECS/ELINCS replaced by REACH

Australia: Australian Inventory of Chemical Substances (AICS)

New Zealand: New Zealand Inventory of Chemicals (NZIoC)

Korea: Korean Existing Chemicals List (KECL)

Japan: Japanese Inventory of Existing and New Chemical Substances (ENCS)

The Philippines: Philippines Inventory of Chemicals and Chemical Substances (PICCS)

China: Inventory of Existing Chemical Substances Manufactured or Imported in China (IECSC)

Taiwan: Existing Chemical Substances Inventory (ECSI)

This product pass through the tests of Skins Sensitization, Skin irritation and cytotoxicity.

Product Stewardship Information 產品責任資訊

The values quoted here are typical of the grade, however, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process.

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。

