



Globalene GL0043D

Polypropylene Composites 聚丙烯複合材料

Features 特性:

- Good Weather Resistance 耐候性佳
- High Dimension Stability @High Temp. 高耐熱尺寸安定性

Typical Application 一般應用:

- Intravenous (IV) Bottle Outer Cap 輸液瓶外蓋

Typical Properties

一般性質

Melt flow rate 熔融流動指數 2.16 kg@230°C

Density 密度

Tensile strength @ yield 降伏點抗張強度

Tensile elongation @ yield 降伏點抗張伸長率

Flexural modulus 彎曲彈性係數

Hardness 表面硬度

Test Method

測試方法

ASTM D1238L

ASTM D792

ASTM D638

ASTM D638

ASTM D790

ASTM D2240

Unit

單位

g/10min.

g/cm³

Kg/cm²

%

Kg/cm²

shore D

Value

數值

33

0.89

86

60

1850

44

Packing 包裝: 25kg/pk

Product Stewardship Information 產品責任資訊

Disclaimer

The values quoted here are typical of the grade and obtained from LCY lab. However, it is important to recognize that some variation around these values is to be expected as a result of uncertainties associated with measurement of the specific property and due to the normal variations encountered during the manufacturing process. We hope above information is sufficient. Because of possible changes in the law and in the regulations, we recommend that customers continuing to use our products verify status every year from this date. We cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products may be used. We accept no responsibility for the results obtained by the application of this information or the safety and suitability of our products alone or in combination with other products. Before using a LCY product, customers and other users should make their own independent determination that the product is suitable for the intended use. They should also ensure that they can use the LCY product safely and legally. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. No one is authorized to make such warranties or assume any liabilities on behalf of LCY except in writing signed by an authorized LCY employee. In no event shall LCY be liable for special, consequential, incidental, punitive, or exemplary damages.

免責聲明:

以上所列之各項數據為實驗參考值，唯因使用時加工條件及環境之不同，而產生之差異非本公司所能保證與控制。我們希望以上信息是足夠的。由於法律法規的可能更改，我們建議持續使用我們產品的客戶從即日起應每年驗證產品狀況。我們不能預期所有條件，並在這些條件下，此信息和我們的產品或是我們的產品與其他製造商產品的組合能夠使用。我們對通過應用此信息所獲得的結果或我們產品單獨或與其他產品組合的安全性和適用性不承擔任何責任。在使用 LCY 產品之前，客戶和其他用戶應自行決定該產品是否適合預期用途。他們還應確保他們可以安全和合法地使用 LCY 產品。本文檔不構成明示或暗示的保證，包括適銷性或適用於特定用途的保證。除由授權的 LCY 員工簽署書面文件外，任何人均無權代表 LCY 作出此類保證或承擔任何責任。在任何情況下，LCY 均不對特殊性，後果性，偶然性，懲罰性或懲戒性的損害承擔責任。

Apr. 2022

台北公司 · 105 臺北市八德路四段 85 號 3 樓

Taipei Office: 3F, 85, Sec. 4, Bade Road,

Taipei 105, Taiwan, ROC

Tel · 886-2-25288895 Fax · 886-2-25288823

大社廠 · 815 高雄市大社區經建路 2 號

Dashe Plant: No. 2, Jingjian Road, Dashe District,

Kaohsiung City 815, Taiwan, ROC

Tel · 886-7-3513211 Fax · 886-7-3515424

