



Technical Data Sheet / 技术数据表


2022/05/05

Globalene 8691		Polypropylene Advanced Material 聚丙烯改性材料	
Features 特性: • High flow rate 高流动性 • Good transparency 良好透明性 • Good balance of stiffness and toughness 良好刚性与韧性的平衡		Typical Application 一般应用: • Injection: container, appliance housing, thin-walled part 置物箱、家电外壳、薄壁产品	
Typical Property 一般性质	Test Method 测试方法	Unit 单位	Value 数值
Melt flow rate (230°C, 2.16kg) 熔融流率	ASTM D1238	g/10min	27
Density 密度	ASTM D792	g/cm ³	0.900
Elongation at yield 降伏点伸张率	ASTM D638	%	15
Elongation at break 断裂点伸张率	ASTM D638	%	750
Tensile strength at yield 降伏点抗张强度	ASTM D638	kg/cm ²	270
Flexural modulus 弯曲弹性系数	ASTM D790	kg/cm ²	9300
Rockwell hardness 洛氏硬度	ASTM D785	R scale	76
Heat deflection temperature (4.6 kg/cm ²) 热变形温度	ASTM D648	°C	72
Izod impact strength, notched 23°C 艾氏冲击强度, 切口 23°C	ASTM D256	kg-cm/cm	13
Mold shrinkage 收缩率	ASTM D955	%	1.4

UL Environmental Claim Validation Mark 环境节能标章

The qualified PP pellets have an UL environmental claim validation mark and enable an average of 10 % energy savings for production of clarified PP parts.

本公司所生产聚丙烯(塑料粒)符合 UL 环境节能标章, 可于透明 PP 对象之生产过程中达到平均约 10 %之节能效益。



Storage and Handling 储放与处置

The inspected and qualified PP pellets will have a shelf life of minimum two years which is estimated from production date, if it is stored at LCY's best condition of proper temperature below 40°C, adequate humidity below 80%, complete package and indoor warehouse with specific protection from damage. However customers might not fully follow the recommendation to conduct the optimal storage condition, the shelf life is recommended six months only at customer site as received.

本公司所生产聚丙烯(塑料粒)经首次产品验证程序确认质量后, 在适合的温度(低于 40° C)、适当的湿度(低于 80%)、包装袋完整、且具有防护设备的仓库储存下, 其有效使用期限至少 2 年(以制造日期起算)。考虑客户端的储存条件可能无法完全依照本公司建议来执行, 客户在购入聚丙烯产品(塑料粒)后, 保存期限建议最高为 6 个月。

Disclaimer 免责声明

- The values quoted here are typical of the grade. It should not be construed as specification.
这里引用的是该牌号的典型值。它不应该被解释为产品规格/规范。
- Ultimately customers must make their own independent determination that these products are suitable for the intended use, and their use of our product is safe, lawful (except as provided in the above information) and technically suitable in their intended applications.
客户必须根据其预期或打算的最终成品用途, 来判断与决定列于此的产品(材料)是适合的, 并且考虑到这样的材料与用途组合不仅能符合相关安全与法规要求(除了以上提供的数据外), 并且也满足在技术层面的需求。

