

Optema™ TC 120 ExCo

Ethylene Methyl Acrylate Copolymer Resin

Product Description

Optema TC 120 is an ethylene methyl acrylate copolymer intended for extrusion coating, coextrusion coating and extrusion lamination where good interlayer adhesion between polyethylene, polypropylene, nylon, PVdC or other substrates is required. It offers excellent balance of adhesion onto the substrates and interlayer adhesion with coextruded LDPE and EVA's. It is an excellent heat seal layer in coextrusion and in extrusion coating but additional additives or process modifications may be required to prevent chill roll sticking. Processing Conditions: Excellent results are obtained in extrusion coating at 260°C to 300°C (500°F - 572°F) temperature range. Processing temperatures above 320°C (608°F) are not recommended. Optema EMA can be processed on conventional extrusion equipment designed for extrusion coating LDPE. Their broad thermal stability range offers wide processing conditions window. Water cooling of extruder throat is preferred to avoid hopper bridging. Matte chill roll finishing is recommended for top coating.

General

Availability ¹	Latin America	North America	
Additive	Antiblock: No	Slip: No	Thermal Stabilizer: Yes
Applications	Coextrusion Coating Demanding Heat Seals Document Plastification	Extrusion Coating Extrusion Lamination Food packaging	Industrial Packaging Non-Woven Coating Thermal Lamination
Revision Date	03/01/2010		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.942 g/cm ³	0.942 g/cm ³	ExxonMobil Method
Melt Index (190°C/2.16 kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Methyl Acrylate Content	21.5 wt%	21.5 wt%	ExxonMobil Method
Peak Melting Temperature	172 °F	78 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	117 °F	47 °C	ASTM D1525

Coating Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Draw Down			
Constant output at 35 rpm, 563°F (295°C)	400 m/min	400 m/min	ExxonMobil Method
Neck-in			
328 ft/min (100 m/min), Constant output at 35 rpm, 563°F (295°C)	2.4 in	6.1 cm	ExxonMobil Method
656 ft/min (200 m/min), Constant output at 35 rpm, 563°F (295°C)	2.2 in	5.6 cm	

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

Typical values obtained on a pilot coextrusion coating line at ExxonMobil Europe Technical Center at an air gap of 170 mm (6.69 in).

Notes


Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +852-6957-5415
Research Center Tel.+188 1699 6168



Live Date: 03/01/2010



Page:

Optema™ TC 120 ExCo
Ethylene Methyl Acrylate Copolymer Resin

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2015 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

HongRong Engineering Plastics Co.,Ltd.
Head Office Tel. +85-2-6957-5415
Research Center Tel.+188 1699 6168