

# Escorene™ Ultra FL 00206

## Ethylene Vinyl Acetate Copolymer Resin

### Product Description

FL 00206 is a copolymer of ethylene and vinyl acetate. Processing Conditions Processing temperatures above 280 °C (536 °F) may cause resin degradation. Machines should always be purged with LDPE or a suitable cleaning compound before shutdown.

### General

Availability <sup>1</sup>	▪ Africa & Middle East	▪ Asia Pacific	▪ Europe
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: No
Applications	▪ Co-Extrusion Films ▪ Form Fill And Seal Packaging	▪ Injection Molding ▪ Skin Packaging	
Revision Date	▪ 03/01/2010		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.925 g/cm <sup>3</sup>	0.925 g/cm <sup>3</sup>	ExxonMobil Method
Melt Index (190°C/2.16 kg)	2.5 g/10 min	2.5 g/10 min	ASTM D1238
Vinyl Acetate Content	6.5 wt%	6.5 wt%	ExxonMobil Method
Peak Melting Temperature	212 °F	100 °C	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	178 °F	81 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Modulus	15000 psi	110 MPa	ISO 527-2/1A/1
Tensile Strain at Break	> 100 %	> 100 %	ISO 527-2/1A
Shore Hardness (Shore A)	94	94	ISO 868

Film Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break MD	3500 psi	24 MPa	ASTM D882
Tensile Strength at Break TD	3200 psi	22 MPa	ASTM D882
Elongation at Break MD	400 %	400 %	ASTM D882
Elongation at Break TD	600 %	600 %	ASTM D882
Secant Modulus MD - 1% Secant	17000 psi	120 MPa	ASTM D882
Secant Modulus TD - 1% Secant	20000 psi	140 MPa	ASTM D882
Dart Drop Impact	280 g	280 g	ASTM D1709A
Elmendorf Tear Strength MD	130 g	130 g	ASTM D1922
Elmendorf Tear Strength TD	130 g	130 g	ASTM D1922

### Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

### Processing Statement

Film properties were measured on a 50 µm (1.97 mil) film extruded on a conventional LDPE extruder. (Extruder screw diameter : 60 mm (2.36 in), rotating die diameter : 200 mm (7.87 in), die gap : 1 mm (39.4 mil), BUR : 2:1, die temperature : 180°C, 356°F) The molded properties were measured on 4 mm (157.5 mil) thick injection molded specimen based on ISO 1872-2.

### Notes

Typical properties: these are not to be construed as specifications.

Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra FL 00206  
Ethylene Vinyl Acetate Copolymer Resin

©2015 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

HongRong Engineering Plastics Co.,Ltd.  
Head Office Tel. +85-2-6957-5415  
Research Center Tel.+188 1699 6168