

Escorene™ Ultra UL 7760

Ethylene Vinyl Acetate Copolymer Resin

Product Description

Escorene Ultra UL 7760 is a high viscosity, 26.7% VA copolymer that has very good flexibility and low temperature toughness. It has good compatibility with both hydrocarbon and natural tackifiers and most waxes, and is suitable for making hot melt adhesives, sealants and wax blends.

General

Availability ¹	▪ Asia Pacific	▪ Latin America	▪ North America
Additive	▪ Antiblock: No	▪ Slip: No	▪ Thermal Stabilizer: Yes
Applications	▪ Adhesives and Sealants ▪ Bonding Adhesives	▪ Hot Melt Adhesives ▪ Industrial Sealants	▪ Wax Blends
Form(s)	▪ Pellets		
Revision Date	▪ 03/01/2010		

Resin Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.954 g/cm ³	0.954 g/cm ³	ASTM D1505
Melt Index (190°C/2.16 kg)	5.7 g/10 min	5.7 g/10 min	ASTM D1238
Vinyl Acetate Content	26.7 wt%	26.7 wt%	ExxonMobil Method
Peak Melting Temperature	163 °F	73 °C	ExxonMobil Method

Thermal

	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	115 °F	46 °C	ASTM D1525

Molded Properties

	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Break	1200 psi	8.3 MPa	ASTM D638
Elongation at Break	> 800 %	> 800 %	ASTM D638
Flexural Modulus - 1% Secant	4100 psi	28 MPa	ASTM D790
Durometer Hardness			ASTM D2240
Shore A, 15 sec	76	76	
Shore D, 15 sec	27	27	

Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

Processing Statement

The test specimens were prepared using ASTM D4703, Procedure C.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

Escorene™ Ultra UL 7760
Ethylene Vinyl Acetate Copolymer Resin

©2015 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

