

# ExxonMobil™ HDPE HD 6908 Series

## High Density Polyethylene Resin

### Product Description

HD 6908 is a homopolymer with outstanding stiffness with a good balance of processability and cold temperature impact performance. This resin is ideally suited for articles requiring very high stiffness or enable down-gauging. This material offers excellent performance in structural foam articles.

### General

Availability <sup>1</sup>	▪ North America		
Additive	▪ HD 6908.65: Antioxidant: Yes; UV Stabilizer: Yes	▪ HD 6908.19: Antioxidant: Yes; UV Stabilizer: No	
Applications	▪ Cases ▪ Crates ▪ Hot Fill Packaging Pails	▪ Materials Handling Articles ▪ Pallets ▪ Structural Foam Articles	▪ Totes Bins
Revision Date	▪ 03/13/2015		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.965 g/cm <sup>3</sup>	0.965 g/cm <sup>3</sup>	ASTM D1505
Melt Index (190°C/2.16 kg)	8.2 g/10 min	8.2 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	189 °F	87 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	119 °F	49 °C	ASTM D648B
Peak Melting Temperature	275 °F	135 °C	ASTM D3418

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	4400 psi	30 MPa	ASTM D638
Elongation at Break	440 %	440 %	ExxonMobil Method
Flexural Modulus			ASTM D790B
1% Secant	270000 psi	1900 MPa	
2% Secant	230000 psi	1600 MPa	
Environmental Stress-Crack Resistance 10% Igepal, F50	3 hr	3 hr	ASTM D1693B

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Notched Izod Impact (-40°F (-40°C))	0.89 ft-lb/in	47 J/m	ASTM D256

### Additional Information

- Properties are based on compression molded samples.
- Test procedures may be modified to accommodate operating conditions or facility limitations.
- Tensile Strength at Yield and Elongation at Break tested using ASTM D638 Type IV, 50 mm/min.

### Legal Statement

This product is not intended for use in medical applications and should not be used in any such applications.

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

