

# Paxon™ 7000 XL Series

## High Density Polyethylene Resin

### Product Description

Paxon™ 7000 series of crosslinkable mHDPE resins are designed to offer outstanding ESCR, toughness, thermal, impact and notch failure resistance. These resins are ideally suited for applications that require excellent part fill during processing and outstanding finished part performance. Paxon™ 7000 series grades are all supplied with long term UV stabilization.

### Key Features

- AddPacks:
- Paxon™ 7003 (Natural) - Pellet
- Paxon™ 7004 (Natural) - 20 and 35 US Mesh Powders
- Paxon™ 7203 (Black) - Pellet
- Paxon™ 7204 (Black) - 20 and 35 US Mesh Powders

### General

Availability <sup>1</sup>	Latin America	North America	
Applications	<ul style="list-style-type: none"> <li>Agricultural Products</li> <li>Automotive Components</li> </ul>	<ul style="list-style-type: none"> <li>Chemical Storage Tanks</li> <li>Large Refuse Containers</li> </ul>	<ul style="list-style-type: none"> <li>Marine Fuel Tanks</li> <li>Recreational Vehicle - Fuel Tanks</li> </ul>
Revision Date	01/13/2016		

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Crosslink Potential	2.5	2.5	ExxonMobil Method

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Deflection Temperature Under Load (DTUL) at 66psi - Unannealed	142 °F	61 °C	ASTM D648
Deflection Temperature Under Load (DTUL) at 264psi - Unannealed	99 °F	37 °C	ASTM D648

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield 2.0 in/min (50 mm/min)	2800 psi	19 MPa	ASTM D638
Elongation at Yield (2.0 in/min (50 mm/min))	20 %	20 %	ASTM D638
Elongation at Break	710 %	710 %	ExxonMobil Method
Flexural Modulus - 1% Secant	87000 psi	600 MPa	ASTM D790B
Environmental Stress-Crack Resistance 10% Igepal, F0 100% Igepal, F0	<ul style="list-style-type: none"> <li>&gt; 1000 hr</li> <li>&gt; 1000 hr</li> </ul>	<ul style="list-style-type: none"> <li>&gt; 1000 hr</li> <li>&gt; 1000 hr</li> </ul>	ASTM D1693

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Impact Strength -40°F (-40°C), 0.125 in (3.18 mm)	75 ft-lb	102 J	ARM
-40°F (-40°C), 0.250 in (6.35 mm)	190 ft-lb	258 J	

### Additional Information

- All physical properties were measured on 3 mm rotomolded samples unless a different value is shown, except for ESCR, which was measured on compression molded samples.
- Test procedures may be modified to accommodate operating conditions or facility limitations.

### Legal Statement

This product is not intended for use in food contact application.

This product is not intended for use in medical applications and should not be used in any such applications.

### Notes

Typical properties: these are not to be construed as specifications.

<sup>1</sup> Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

