

Paxon™ AF50-003

High Density Polyethylene Resin

Product Description

AF50-003 is a blow molding grade high density polyethylene copolymer containing an antistatic additive. It offers very good balance of stress crack resistance, stiffness and impact strength.

General

Availability ¹	<ul style="list-style-type: none"> Latin America North America
Additive	<ul style="list-style-type: none"> Thermal Stabilizer: Yes Antistatic: Yes
Applications	<ul style="list-style-type: none"> Food Packaging Household and Industrial chemical containers Pharmaceutical Packaging Thermoformed Parts Thin Gauge Sheet
Revision Date	<ul style="list-style-type: none"> 03/01/2010

Resin Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Density	0.950 g/cm ³	0.950 g/cm ³	ASTM D4883
Melt Index (190°C/2.16 kg)	0.33 g/10 min	0.33 g/10 min	ASTM D1238

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Brittleness Temperature	< -105 °F	< -76 °C	ASTM D746
Vicat Softening Temperature	255 °F	124 °C	ASTM D1525

Molded Properties	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Strength at Yield	3900 psi	27 MPa	ASTM D638
Flexural Modulus	170000 psi	1200 MPa	ASTM D790
Environmental Stress-Crack Resistance 100% Igepal	70 hr	70 hr	ASTM D1693

Impact	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Impact Strength	90 ft-lb/in ²	190 kJ/m ²	ASTM D1822

Legal Statement

Contact your ExxonMobil Chemical Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB).

This product is not intended for use in medical applications and should not be used in any such applications.

Processing Statement

1. Values may change with future development. 2. All molded properties were measured on compression molded plaques. 3. Flexural modulus tested using Procedure A (1"x3"x0.125"), tangent calculation. 4. ESCR tested using Condition B, 100% Igepal. 5. AF50-003 has NSF recognition. Contact your ExxonMobil Chemical representative for details.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

