

Vistamaxx™ 7050FL

Performance Polymer


Product Description

Vistamaxx 7050FL performance polymer is an olefinic elastomer chiefly composed of isotactic propylene repeat units with random ethylene distribution, and is produced using ExxonMobil Chemical's proprietary metallocene catalyst technology. The 'FL' designates this product passes ExxonMobil Chemical's test for film appearance with regard to gels, as needed for performance film applications ('A' rating).

Key Features

- Applicable for hygiene and nonwoven applications, including those that require elasticity.
- Suitable for spunbond and meltblown nonwoven processes.
- Can be blended with PE, PP and other polymers, including styrenic block copolymers.
- Excellent adhesion to conventional and metallocene PP and PE.
- Good chemical resistance to aqueous systems and non-hydrocarbon based fluids.
- RoHS compliant.

First Cycle Hysteresis



General

Availability ¹	<ul style="list-style-type: none"> ▪ Africa & Middle East ▪ Asia Pacific 	<ul style="list-style-type: none"> ▪ Europe ▪ Latin America 	<ul style="list-style-type: none"> ▪ North America
Applications	<ul style="list-style-type: none"> ▪ Elastic Hygiene Film ▪ Meltblown Nonwovens 	<ul style="list-style-type: none"> ▪ Nonwovens and Laminates ▪ Spunbond Nonwovens 	
Uses	<ul style="list-style-type: none"> ▪ Hygiene 	<ul style="list-style-type: none"> ▪ Nonwovens 	<ul style="list-style-type: none"> ▪ Personal Care
RoHS Compliance	<ul style="list-style-type: none"> ▪ RoHS Compliant 		
Form(s)	<ul style="list-style-type: none"> ▪ Pellets 		
Revision Date	<ul style="list-style-type: none"> ▪ 07/23/2015 		

Elastomer Curves	Typical Value (English)	Typical Value (SI)	Test Based On
First Cycle Retractive Force	3.2 lbf	14 N	ExxonMobil Method
First Cycle Load Loss	53 %	53 %	ExxonMobil Method
First Cycle Permanent Set	10 %	10 %	ExxonMobil Method
First Cycle Mechanical Hysteresis	50 %	50 %	ExxonMobil Method

Physical	Typical Value (English)	Typical Value (SI)	Test Based On
Density ²	0.865 g/cm ³	0.865 g/cm ³	ASTM D1505
Melt Index ² (190°C/2.16 kg)	20 g/10 min	20 g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) ² (230°C/2.16 kg)	48 g/10 min	48 g/10 min	ASTM D1238
Ethylene Content	13 wt%	13 wt%	ExxonMobil Method



Vistamaxx™ 7050FL
Performance Polymer

Mechanical	Typical Value (English)	Typical Value (SI)	Test Based On
Tensile Stress at 100%	394 psi	2.71 MPa	ASTM D638
Tensile Stress at 300%	410 psi	2.83 MPa	ASTM D638
Tensile Strength at Break	> 1400 psi	> 9.65 MPa	ASTM D638
Tensile Set (73°F (23°C))	14 %	14 %	ExxonMobil Method
Elongation at Break	> 1900 %	> 1900 %	ASTM D638
Flexural Modulus - 1% Secant	2980 psi	20.5 MPa	ASTM D790

Thermal	Typical Value (English)	Typical Value (SI)	Test Based On
Vicat Softening Temperature	125 °F	51.5 °C	ExxonMobil Method

Additional Information

In accordance with FDA Food Contact Notification (FCN) 936, this product may be used as articles or component of articles used in contact with all food types under Conditions of Use C through G, as described in Table 2 of 21 CFR 176.170(c).

The base resin in this product is listed in the Chinese Positive List for allowed resins in food packaging materials (issued by China MoH, 11 Oct 2011) and additives that may be present in this product are authorized according to the National Standard of People's Republic of China GB9685-2008, Hygienic Standards for Uses of Additives in Food Containers and Packaging Materials.

EU Note: The composition of this product complies with the requirements for use in contact with food of EU Regulation 10/2011.

Please contact Customer Service for the official food law certificates which provide more detailed information.

Legal Statement

This product, including the product name, shall not be used or tested in any medical application without the prior written acknowledgement of ExxonMobil Chemical as to the intended use.

For detailed Product Stewardship information, please contact Customer Service.

Processing Statement

Vistamaxx performance polymer has a wide temperature processing window. A good starting point for temperatures is 10°C above the highest melting point. This material does not require drying and can be compounded or used in a dry blend. Use conventional processing knowledge to ensure mixing of the materials.

Notes

Typical properties: these are not to be construed as specifications.

¹ Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete Country Availability.

² Property specified in conventional unit of measure.

For additional technical, sales and order assistance: www.exxonmobilchemical.com/ContactUs

©2015 ExxonMobil. ExxonMobil, the ExxonMobil logo, the interlocking "X" device and other product or service names used herein are trademarks of ExxonMobil, unless indicated otherwise. This document may not be distributed, displayed, copied or altered without ExxonMobil's prior written authorization. To the extent ExxonMobil authorizes distributing, displaying and/or copying of this document, the user may do so only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. You may not copy this document to or reproduce it in whole or in part on a website. ExxonMobil does not guarantee the typical (or other) values. Any data included herein is based upon analysis of representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, suitability, accuracy, reliability, or completeness of this information or the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. This document is not an endorsement of any non-ExxonMobil product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "ExxonMobil Chemical" and "ExxonMobil" are each used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliate either directly or indirectly stewarded.

